

# Stainless steels —

## Part 1: List of stainless steels

The European Standard EN 10088-1:2005 has the status of a British Standard

ICS 77.140.20

## National foreword

This British Standard is the official English language version of EN 10088-1:2005. It supersedes BS EN 10088-1:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/30, Stainless Steels, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

This second edition of BS EN 10088-1 is a revised reference document containing chemical analysis and physical property data for 160 stainless steels plus 18 nickel and cobalt alloys.

BS EN 10088 is published in three parts. Two further parts of this series (prEN 10088-4 and prEN 10088-5) are currently in preparation and have been designed to meet the needs of the Construction Products Directive (CPD).

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 38, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 June 2005

© BSI 30 June 2005

ISBN 0 580 46335 4

### Amendments issued since publication

Amd. No.	Date	Comments

English version

## Stainless steels - Part 1: List of stainless steels

Aciers inoxydables - Partie 1: Liste des aciers inoxydables

Nichtrostende Stähle - Teil 1: Verzeichnis der  
nichtrostenden Stähle

This European Standard was approved by CEN on 14 April 2005.

CEN members are bound to comply with the CEN/GENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

Page

Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	5
4 Chemical composition .....	5
Annex A (informative) Guidance data on some physical properties .....	17
Annex B (informative) Classification of stainless steel grades.....	26
Annex C (informative) Empirical formulae for steel grade classification by microstructure .....	30
Annex D (informative) Matrix to show which steels are included in which standards .....	31
Annex E (informative) Chemical composition of nickel and cobalt alloys listed in EN 10095, EN 10269 and EN 10302 .....	35
Bibliography .....	37

## Foreword

This European Standard (EN 10088-1:2005) has been prepared by Technical Committee ECISS/TC 23 "Steels for heat treatment, alloy steels and free-cutting steels - Qualities and dimensions", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2005, and conflicting national standards shall be withdrawn at the latest by December 2005.

This document supersedes EN 10088-1:1995.

EN 10088, under the general title "Stainless steels", consists of the following parts:

- Part 1: List of stainless steels (including a table of European Standards, in which these stainless steels are further specified, see Annex D),
- Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes,
- Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes.

The European Organisation for Standardisation (CEN) draws attention to the fact that it is claimed that compliance with this document may involve the use of patents applied to five steels grades

CEN takes no position concerning the evidence, validity and scope of these patent rights.

The holder of these patent rights has assured CEN that they are willing to negotiate licences, under reasonable and non-discriminatory terms and conditions, with applicants throughout the world. In this respect, the statements of the holders of these patent rights are registered with CEN. Information may be obtained from:

Grades 1.4362, 1.4410 and 1.4477

Sandvik AB  
SE-811 81 SANDVIKEN  
Sweden

Grades 1.4652, 1.4854

Outokumpu Stainless AB  
SE-77480 AVESTA  
Sweden

Attention is drawn to the possibility that some of the elements within this document may be the subject of patent rights other than those indicated above. CEN shall not be responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## 1 Scope

This European Standard lists the chemical composition of stainless steels, which are subdivided in accordance with their main properties into corrosion resisting steels, heat resisting steels and creep resisting steels and specified in the European Standards given in Table 1.

**Table 1 — Overview of material standards for stainless steels**

Stainless steels		
Corrosion resisting steels	Heat resisting steels	Creep resisting steels
EN 10028-7		EN 10028-7
EN 10088-2		
EN 10088-3		
	EN 10095	
EN 10151		
EN 10216-5		EN 10216-5
EN 10217-7		
EN 10222-5		EN 10222-5
EN 10250-4		
EN 10263-5		
EN 10264-4	EN 10264-4	
EN 10269		EN 10269
EN 10270-3		
EN 10272		
EN 10296-2		
EN 10297-2		
		EN 10302
EN 10312		

Reference data on some physical properties are given in Tables A.1 to A.8.

NOTE 1 A matrix that shows which steels are included in which standard is given in Annex D.

NOTE 2 Valve steels are specified in EN 10090.

NOTE 3 Steel castings are specified in various European Standards (see Bibliography).

NOTE 4 Tool steels are specified in EN ISO 4957.

NOTE 5 Welding consumables are specified in various European Standards (see Bibliography).

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10079:1992, *Definition of steel products*

EN 10020:2000, *Definition and classification of grades of steel*

### 3 Terms and definitions

For the purposes of this European Standard, the terms and definitions for the product forms given in EN 10079:1992 and the following apply.

#### 3.1

##### **stainless steels**

stainless steels are steels with at least 10,5 % of chromium and maximum 1,2 % of carbon

[see EN 10020:2000, definition 3.2.2]

They are further subdivided in accordance with their main property into corrosion resisting steels, heat resisting steels and creep resisting steels

NOTE One steel in Table 6 and five in Table 8 contain less Chromium than the minimum defined for stainless steels, but are included in the heat-resisting and creep-resisting steels standards respectively, because they form a part of these two families of steels.

### 4 Chemical composition

The chemical composition of stainless steels is given

- in Table 2 for ferritic corrosion resisting steels;
- in Table 3 for martensitic and precipitation hardening corrosion resisting steels;
- in Table 4 for austenitic corrosion resisting steels;
- in Table 5 for austenitic-ferritic corrosion resisting steels;
- in Table 6 for ferritic heat resisting steels;
- in Table 7 for austenitic and austenitic-ferritic heat resisting steels;
- in Table 8 for martensitic creep resisting steels;
- in Table 9 for austenitic creep resisting steels.

NOTE The chemical composition of nickel and cobalt alloys listed in EN 10095, EN 10269 and EN 10302 is given in Tables E.1 and E.2.

Table 2 — Chemical composition (cast analysis) <sup>a</sup> of ferritic corrosion resisting steels

Steel designation		% by mass											
Name	Number	C max.	Si max.	Mn max.	P max.	S	N max.	Cr	Mo	Nb	Ni	Ti	Others
X2CrNi12	1.4003	0,030	1,00	1,50	0,040	≤ 0,015 <sup>b</sup>	0,030	10,5 to 12,5	-	-	0,30 to 1,00	-	-
X2CrTi12	1.4512	0,030	1,00	1,00	0,040	≤ 0,015	-	10,5 to 12,5	-	-	-	[6 x (C+N)] to 0,65	-
X6CrNiTi12	1.4516	0,08	0,70	1,50	0,040	≤ 0,015	-	10,5 to 12,5	-	-	0,50 to 1,50	0,05 to 0,35	-
X6Cr13	1.4000	0,08	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	12,0 to 14,0	-	-	-	-	-
X6CrAl13	1.4002	0,08	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	12,0 to 14,0	-	-	-	-	Al : 0,10 to 0,30
X2CrTi17	1.4520	0,025	0,50	0,50	0,040	≤ 0,015	0,015	16,0 to 18,0	-	-	-	0,30 to 0,60	-
X6Cr17	1.4016	0,08	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	16,0 to 18,0	-	-	-	-	-
X3CrTi17	1.4510	0,05	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	16,0 to 18,0	-	-	-	[4 x (C+N) + 0,15] to 0,80 <sup>c</sup>	-
X1CrNb15	1.4595	0,020	1,00	1,00	0,025	≤ 0,015	0,020	14,0 to 16,0	-	0,20 to 0,60	-	-	-
X3CrNb17	1.4511	0,05	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	16,0 to 18,0	-	12 x C to 1,00	-	-	-
X6CrMo17-1	1.4113	0,08	1,00	1,00	0,040	≤ 0,015 <sup>b</sup>	-	16,0 to 18,0	0,90 to 1,40	-	-	-	-
X6CrMoS17	1.4105	0,08	1,50	1,50	0,040	0,15 to 0,35	-	16,0 to 18,0	0,20 to 0,60	-	-	-	-
X2CrMoTi17-1	1.4513	0,025	1,00	1,00	0,040	≤ 0,015	0,020	16,0 to 18,0	0,80 to 1,40	-	-	0,30 to 0,60	-
X2CrMoTi18-2	1.4521	0,025	1,00	1,00	0,040	≤ 0,015	0,030	17,0 to 20,0	1,80 to 2,50	-	-	[4 x (C+N) + 0,15] to 0,80 <sup>c</sup>	-
X2CrMoTiS18-2	1.4523	0,030	1,00	0,50	0,040	0,15 to 0,35	-	17,5 to 19,0	2,00 to 2,50	-	-	0,30 to 0,80	(C+N) ≤ 0,040
X6CrNi17-1	1.4017	0,08	1,00	1,00	0,040	≤ 0,015	-	16,0 to 18,0	-	-	1,20 to 1,60	-	-
X5CrNiMoTi15-2	1.4589	0,08	1,00	1,00	0,040	≤ 0,015	-	13,5 to 15,5	0,20 to 1,20	-	1,00 to 2,50	0,30 to 0,50	-
X6CrMoNb17-1	1.4526	0,08	1,00	1,00	0,040	≤ 0,015	0,040	16,0 to 18,0	0,80 to 1,40	[7x(C+N)+0,10] to 1,00	-	-	-
X2CrNbZr17	1.4590	0,030	1,00	1,00	0,040	≤ 0,015	-	16,0 to 17,5	-	0,35 to 0,55	-	-	Zr ≥ 7x(C+N)+0,15
X2CrTiNb18	1.4509	0,030	1,00	1,00	0,040	≤ 0,015	-	17,5 to 18,5	-	[3 x C + 0,30] to 1,00	-	0,10 to 0,60	-
X2CrMoTi29-4	1.4592	0,025	1,00	1,00	0,030	≤ 0,010	0,045	28,0 to 30,0	3,50 to 4,50	-	-	[4 x (C+N) + 0,15] to 0,80 <sup>c</sup>	-

<sup>a</sup> Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

<sup>b</sup> For bars, rods, wire, sections, bright products and the relevant semi-finished products, a maximum content of 0,030 % S applies. Particular ranges of sulphur content may provide improvement of particular properties. For machinability a controlled sulphur content of 0,015 % to 0,030 % is recommended and permitted. For weldability, a controlled sulphur content of 0,008 % to 0,030 % is recommended and permitted. For polishability, a controlled sulphur content of 0,015 % max. is recommended.

<sup>c</sup> The stabilisation may be made by use of titanium or niobium or zirconium. According to the atomic mass of these elements and the content of carbon and nitrogen, the equivalence shall be the following:  
 $Nb$  (% by mass)  $\equiv$   $Zr$  (% by mass)  $\equiv$   $7/4 Ti$  (% by mass).



Table 3 — Chemical composition (cast analysis)<sup>a</sup> of martensitic and precipitation hardening corrosion resisting steels

Steel designation		% by mass										
Name	Number	C <sup>c</sup>	Si max.	Mn	P max.	S	Cr	Cu	Mo	Nb	Ni	Others
X12Cr13	1.4006	0,08 to 0,15	1,00	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	11,5 to 13,5	-	-	-	≤ 0,75	-
X12CrS13	1.4005	0,08 to 0,15	1,00	≤ 1,50	0,040	0,15 to 0,35	12,0 to 14,0	-	≤ 0,60	-	-	-
X15Cr13	1.4024	0,12 to 0,17	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	12,0 to 14,0	-	-	-	-	-
X20Cr13	1.4021	0,16 to 0,25	1,00	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	12,0 to 14,0	-	-	-	-	-
X30Cr13	1.4028	0,26 to 0,35	1,00	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	12,0 to 14,0	-	-	-	-	-
X29CrS13	1.4029	0,25 to 0,32	1,00	≤ 1,50	0,040	0,15 to 0,25	12,0 to 13,5	-	≤ 0,60	-	-	-
X39Cr13	1.4031	0,36 to 0,42	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	12,5 to 14,5	-	-	-	-	-
X46Cr13	1.4034	0,43 to 0,50	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	12,5 to 14,5	-	-	-	-	-
X46CrS13	1.4035	0,43 to 0,50	1,00	≤ 2,00	0,040	0,15 to 0,35	12,5 to 14,0	-	-	-	-	-
X38CrMo14	1.4419	0,36 to 0,42	1,00	≤ 1,00	0,040	≤ 0,015	13,0 to 14,5	-	0,60 to 1,00	-	-	-
X55CrMo14	1.4110	0,48 to 0,60	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	13,0 to 15,0	-	0,50 to 0,80	-	-	V: ≤ 0,15
X50CrMoV15	1.4116	0,45 to 0,55	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	14,0 to 15,0	-	0,50 to 0,80	-	-	V: 0,10 to 0,20
X70CrMo15	1.4109	0,60 to 0,75	0,70	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	14,0 to 16,0	-	0,40 to 0,80	-	-	-
X40CrMoVN16-2	1.4123	0,35 to 0,50	1,00	≤ 1,00	0,040	≤ 0,015	14,0 to 16,0	-	1,00 to 2,50	-	≤ 0,50	V ≤ 1,50 N: 0,10 to 0,30
X14CrMoS17	1.4104	0,10 to 0,17	1,00	≤ 1,50	0,040	0,15 to 0,35	15,5 to 17,5	-	0,20 to 0,60	-	-	-
X39CrMo17-1	1.4122	0,33 to 0,45	1,00	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	15,5 to 17,5	-	0,80 to 1,30	-	≤ 1,00	-
X105CrMo17	1.4125	0,95 to 1,20	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	16,0 to 18,0	-	0,40 to 0,80	-	-	-
X90CrMoV18	1.4112	0,85 to 0,95	1,00	≤ 1,00	0,040	≤ 0,015 <sup>b</sup>	17,0 to 19,0	-	0,90 to 1,30	-	-	V: 0,07 to 0,12
X17CrNi16-2	1.4057	0,12 to 0,22	1,00	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	15,0 to 17,0	-	-	-	1,50 to 2,50	-
X1CrNiMoCu12-5-2	1.4422	≤ 0,020	0,50	≤ 2,00	0,040	≤ 0,003	11,0 to 13,0	0,20 to 0,80	1,30 to 1,80	-	4,0 to 5,0	N: ≤ 0,020
X1CrNiMoCu12-7-3	1.4423	≤ 0,020	0,50	≤ 2,00	0,040	≤ 0,003	11,0 to 13,0	0,20 to 0,80	2,30 to 2,80	-	6,0 to 7,0	N: ≤ 0,020
X2CrNiMoV13-5-2	1.4415	≤ 0,030	0,50	≤ 0,50	0,040	≤ 0,015	11,5 to 13,5	-	1,50 to 2,50	-	4,5 to 6,5	Ti: ≤ 0,010 V: 0,10 to 0,50
X3CrNiMo13-4	1.4313	≤ 0,05	0,70	≤ 1,50	0,040	≤ 0,015	12,0 to 14,0	-	0,30 to 0,70	-	3,5 to 4,5	N: ≥ 0,020
X4CrNiMo16-5-1	1.4418	≤ 0,06	0,70	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	15,0 to 17,0	-	0,80 to 1,50	-	4,0 to 6,0	N: ≥ 0,020
X1CrNiMoAlTi12-9-2	1.4530	≤ 0,015	0,10	≤ 0,10	0,010	≤ 0,005	11,5 to 12,5	-	1,85 to 2,15	-	8,5 to 9,5	Al: 0,60 to 0,80 Ti: 0,28 to 0,37 N: ≤ 0,010
X1CrNiMoAlTi12-10-2	1.4596	≤ 0,015	0,10	≤ 0,10	0,010	≤ 0,005	11,5 to 12,5	-	1,85 to 2,15	-	9,2 to 10,2	Al: 0,80 to 1,10 Ti: 0,28 to 0,40 N: ≤ 0,020
X5CrNiCuNb16-4	1.4542	≤ 0,07	0,70	≤ 1,50	0,040	≤ 0,015 <sup>b</sup>	15,0 to 17,0	3,0 to 5,0	≤ 0,60	5xC to 0,45	3,0 to 5,0	-

Table 3 (concluded)

Steel designation		% by mass										
Name	Number	C <sup>c</sup>	Si max.	Mn	P max.	S	Cr	Cu	Mo	Nb	Ni	Others
X7CrNiAl17-7	1.4568	≤ 0,09	0,70	≤ 1,00	0,040	≤ 0,015	16,0 to 18,0	-	-	-	6,5 to 7,8 <sup>d</sup>	Al: 0,70 to 1,50
X5CrNiMoCuNb14-5	1.4594	≤ 0,07	0,70	≤ 1,00	0,040	≤ 0,015	13,0 to 15,0	1,20 to 2,00	1,20 to 2,00	0,15 to 0,60	5,0 to 6,0	-
X5NiCrTiMoVB25-15-2	1.4606	≤ 0,08	1,00	1,00 to 2,00	0,025	≤ 0,015	13,0 to 16,0	-	1,00 to 1,50	-	24,0 to 27,0	B: 0,001 0 to 0,010 Al: ≤ 0,35 Ti: 1,90 to 2,30 V: 0,10 to 0,50

<sup>a</sup> Elements not quoted in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

<sup>b</sup> For bars, rods, wire, sections, bright products and the relevant semi-finished products, a maximum content of 0,030 % S applies. Particular ranges of sulphur content may provide improvement of particular properties. For machinability a controlled sulphur content of 0,015 % to 0,030 % is recommended and permitted. For weldability, a controlled sulphur content of 0,008 % to 0,030 % is recommended and permitted. For polishability, a controlled sulphur content of 0,015 % max. is recommended.

<sup>c</sup> Tighter carbon ranges may be agreed at the time of enquiry and order.

<sup>d</sup> For better cold deformability, the upper limit may be increased to 8,3 %.

Table 4 — Chemical composition (cast analysis)<sup>a</sup> of austenitic corrosion resisting steels

Steel designation		% by mass											
Name	Number	C	Si	Mn	P max.	S	N	Cr	Cu <sup>c</sup>	Mo	Nb	Ni	Others
X5CrNi17-7	1.4319	≤ 0,07	≤ 1,00	≤ 2,00	0,045	≤ 0,030	≤ 0,11	16,0 to 18,0	-	-	-	6,0 to 8,0	-
X10CrNi18-8	1.4310	0,05 to 0,15	≤ 2,00	≤ 2,00	0,045	≤ 0,015	≤ 0,11	16,0 to 19,0	-	≤ 0,80	-	6,0 to 9,5	-
X9CrNi18-9	1.4325	0,03 to 0,15	≤ 1,00	≤ 2,00	0,045	≤ 0,030	≤ 0,11	17,0 to 19,0	-	-	-	8,0 to 10,0	-
X2CrNi18-7	1.4318	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015	0,10 to 0,20	16,5 to 18,5	-	-	-	6,0 to 8,0	-
X2CrNi18-9	1.4307	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,5 to 19,5	-	-	-	8,0 to 10,5	-
X2CrNi19-11	1.4306	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	18,0 to 20,0	-	-	-	10,0 to 12,0 <sup>d</sup>	-
X5CrNi19-9	1.4315	≤ 0,06	≤ 1,00	≤ 2,00	0,045	≤ 0,015	0,12 to 0,22	18,0 to 20,0	-	-	-	8,0 to 11,0	-
X2CrNi18-10	1.4311	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	0,12 to 0,22	17,5 to 19,5	-	-	-	8,5 to 11,5	-
X5CrNi18-10	1.4301	≤ 0,07	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,5 to 19,5	-	-	-	8,0 to 10,5	-
X8CrNiS18-9 <sup>e</sup>	1.4305 <sup>e</sup>	≤ 0,10	≤ 1,00	≤ 2,00	0,045	0,15 to 0,35	≤ 0,11	17,0 to 19,0	≤ 1,00	-	-	8,0 to 10,0	-
X6CrNiTi18-10	1.4541	≤ 0,08	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	-	17,0 to 19,0	-	-	-	9,0 to 12,0 <sup>d</sup>	Ti:5xC to 0,70
X6CrNiNb18-10	1.4550	≤ 0,08	≤ 1,00	≤ 2,00	0,045	≤ 0,015	-	17,0 to 19,0	-	-	10xC to 1,00	9,0 to 12,0 <sup>d</sup>	-
X4CrNi18-12	1.4303	≤ 0,06	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,0 to 19,0	-	-	-	11,0 to 13,0	-
X1CrNi25-21	1.4335	≤ 0,020	≤ 0,25	≤ 2,00	0,025	≤ 0,010	≤ 0,11	24,0 to 26,0	-	≤ 0,20	-	20,0 to 22,0	-
X2CrNiMo17-12-2	1.4404	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	16,5 to 18,5	-	2,00 to 2,50	-	10,0 to 13,0 <sup>d</sup>	-
X2CrNiMoN17-11-2	1.4406	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	0,12 to 0,22	16,5 to 18,5	-	2,00 to 2,50	-	10,0 to 12,5 <sup>d</sup>	-
X5CrNiMo17-12-2	1.4401	≤ 0,07	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	16,5 to 18,5	-	2,00 to 2,50	-	10,0 to 13,0	-
X1CrNiMoN25-22-2	1.4466	≤ 0,020	≤ 0,70	≤ 2,00	0,025	≤ 0,010	0,10 to 0,16	24,0 to 26,0	-	2,00 to 2,50	-	21,0 to 23,0	-
X6CrNiMoTi17-12-2	1.4571	≤ 0,08	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	-	16,5 to 18,5	-	2,00 to 2,50	-	10,5 to 13,5 <sup>d</sup>	Ti:5xC to 0,70
X6CrNiMoNb17-12-2	1.4580	≤ 0,08	≤ 1,00	≤ 2,00	0,045	≤ 0,015	-	16,5 to 18,5	-	2,00 to 2,50	10xC to 1,00	10,5 to 13,5	-
X2CrNiMo17-12-3	1.4432	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	16,5 to 18,5	-	2,50 to 3,00	-	10,5 to 13,0	-
X2CrNiMoN17-13-3	1.4429	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015	0,12 to 0,22	16,5 to 18,5	-	2,50 to 3,00	-	11,0 to 14,0 <sup>d</sup>	-
X3CrNiMo17-13-3	1.4436	≤ 0,05	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	16,5 to 18,5	-	2,50 to 3,00	-	10,5 to 13,0 <sup>d</sup>	-
X3CrNiMo18-12-3	1.4449	≤ 0,035	≤ 1,00	≤ 2,00	0,045	≤ 0,015	≤ 0,08	17,0 to 18,2	≤ 1,00	2,25 to 2,75	-	11,5 to 12,5	-
X2CrNiMo18-14-3	1.4435	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,0 to 19,0	-	2,50 to 3,00	-	12,5 to 15,0	-
X2CrNiMoN18-12-4	1.4434	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015	0,10 to 0,20	16,5 to 19,5	-	3,0 to 4,0	-	10,5 to 14,0 <sup>d</sup>	-
X2CrNiMo18-15-4	1.4438	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,5 to 19,5	-	3,0 to 4,0	-	13,0 to 16,0 <sup>d</sup>	-
X2CrNiMoN17-13-5	1.4439	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015	0,12 to 0,22	16,5 to 18,5	-	4,0 to 5,0	-	12,5 to 14,5	-
X1CrNiMoCuN24-22-8 <sup>1)</sup>	1.4652 <sup>1)</sup>	≤ 0,020	≤ 0,50	2,00 to 4,0	0,030	≤ 0,005	0,45 to 0,55	23,0 to 25,0	0,30 to 0,60	7,0 to 8,0	-	21,0 to 23,0	-
X1CrNiSi18-15-4	1.4361	≤ 0,015	3,7 to 4,5	≤ 2,00	0,025	≤ 0,010	≤ 0,11	16,5 to 18,5	-	≤ 0,20	-	14,0 to 16,0	-
X11CrNiMnN19-8-6	1.4369	0,07 to 0,15	0,50 to 1,00	5,0 to 7,5	0,030	≤ 0,015	0,20 to 0,30	17,5 to 19,5	-	-	-	6,5 to 8,5	-
X12CrMnNiN17-7-5	1.4372	≤ 0,15	≤ 1,00	5,5 to 7,5	0,045	≤ 0,015	0,05 to 0,25	16,0 to 18,0	-	-	-	3,5 to 5,5	-
X2CrMnNiN17-7-5	1.4371	≤ 0,030	≤ 1,00	6,0 to 8,0	0,045	≤ 0,015	0,15 to 0,20	16,0 to 17,0	-	-	-	3,5 to 5,5	-
X12CrMnNiN18-9-5	1.4373	≤ 0,15	≤ 1,00	7,5 to 10,5	0,045	≤ 0,015	0,05 to 0,25	17,0 to 19,0	-	-	-	4,0 to 6,0	-
X8CrMnNiN18-9-5	1.4374	0,05 to 0,10	0,30 to 0,60	9,0 to 10,0	0,035	≤ 0,030	0,25 to 0,32	17,5 to 18,5	≤ 0,40	≤ 0,50	-	5,0 to 6,0	-
X8CrMnCuNB17-8-3	1.4597	≤ 0,10	≤ 2,00	6,5 to 8,5	0,040	≤ 0,030	0,15 to 0,30	16,0 to 18,0	2,00 to 3,5	≤ 1,00	-	≤ 2,00	B: 0,000 5 to 0,005 0
X3CrNiCu19-9-2	1.4560	≤ 0,035	≤ 1,00	1,50 to 2,00	0,045	≤ 0,015	≤ 0,11	18,0 to 19,0	1,50 to 2,00	-	-	8,0 to 9,0	-
X2CrNiCu19-10	1.4650	≤ 0,030	≤ 1,00	≤ 2,00	0,045	≤ 0,015	≤ 0,08	18,5 to 20,0	≤ 1,00	-	-	9,0 to 10,0	-
X6CrNiCuS18-9-2 <sup>e</sup>	1.4570 <sup>e</sup>	≤ 0,08	≤ 1,00	≤ 2,00	0,045	0,15 to 0,35	≤ 0,11	17,0 to 19,0	1,40 to 1,80	≤ 0,60	-	8,0 to 10,0	-

Table 4 (concluded)

Steel designation		% by mass											
Name	Number	C	Si	Mn	P max.	S	N	Cr	Cu <sup>c</sup>	Mo	Nb	Ni	Others
X3CrNiCu18-9-4	1.4567	≤ 0,04	≤ 1,00	≤ 2,00	0,045	≤ 0,015 <sup>b</sup>	≤ 0,11	17,0 to 19,0	3,0 to 4,0	-	-	8,5 to 10,5	-
X3CrNiCuMo17-11-3-2	1.4578	≤ 0,04	≤ 1,00	≤ 2,00	0,045	≤ 0,015	≤ 0,11	16,5 to 17,5	3,0 to 3,5	2,00 to 2,50	-	10,0 to 11,0	-
X1NiCrMoCu31-27-4	1.4563	≤ 0,020	≤ 0,70	≤ 2,00	0,030	≤ 0,010	≤ 0,11	26,0 to 28,0	0,70 to 1,50	3,0 to 4,0	-	30,0 to 32,0	-
X1NiCrMoCu25-20-5	1.4539	≤ 0,020	≤ 0,70	≤ 2,00	0,030	≤ 0,010	≤ 0,15	19,0 to 21,0	1,20 to 2,00	4,0 to 5,0	-	24,0 to 26,0	-
X1CrNiMoCuN25-25-5	1.4537	≤ 0,020	≤ 0,70	≤ 2,00	0,030	≤ 0,010	0,17 to 0,25	24,0 to 26,0	1,00 to 2,00	4,7 to 5,7	-	24,0 to 27,0	-
X1CrNiMoCuN20-18-7	1.4547	≤ 0,020	≤ 0,70	≤ 1,00	0,030	≤ 0,010	0,18 to 0,25	19,5 to 20,5	0,50 to 1,00	6,0 to 7,0	-	17,5 to 18,5	-
X2CrNiMoCuS17-10-2 <sup>e</sup>	1.4598 <sup>e</sup>	≤ 0,03	≤ 1,00	≤ 2,00	0,045	0,10 to 0,25	≤ 0,11	16,5 to 18,5	1,30 to 1,80	2,00 to 2,50	-	10,0 to 13,0	-
X1CrNiMoCuNW24-22-6	1.4659	≤ 0,020	≤ 0,70	2,00 to 4,0	0,030	≤ 0,010	0,35 to 0,50	23,0 to 25,0	1,00 to 2,00	5,5 to 6,5	-	21,0 to 23,0	W:1,50 to 2,50
X1NiCrMoCuN25-20-7	1.4529	≤ 0,020	≤ 0,50	≤ 1,00	0,030	≤ 0,010	0,15 to 0,25	19,0 to 21,0	0,50 to 1,50	6,0 to 7,0	-	24,0 to 26,0	-
X2NiCrAlTi32-20	1.4558	≤ 0,030	≤ 0,70	≤ 1,00	0,020	≤ 0,015	-	20,0 to 23,0	-	-	-	32,0 to 35,0	Al:0,15 to 0,45 Ti:[8x(C+N)] to 0,60
X2CrNiMnMoN25-18-6-5	1.4565	≤ 0,030	≤ 1,00	5,0 to 7,0	0,030	≤ 0,015	0,30 to 0,60	24,0 to 26,0	-	4,0 to 5,0	≤ 0,15	16,0 to 19,0	-

<sup>a</sup> Elements not quoted in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

<sup>b</sup> For bars, rods, wire, sections, bright products and the relevant semi-finished products, a maximum content of 0,030 % S applies. Particular ranges of sulphur content may provide improvement of particular properties. For machinability a controlled sulphur content of 0,015 % to 0,030 % is recommended and permitted. For weldability, a controlled sulphur content of 0,008 % to 0,030 % is recommended and permitted. For polishability, a controlled sulphur content of 0,015 % max. is recommended.

<sup>c</sup> For austenitic steel grades intended for cold heading and cold extruding, a Cu-content of max. 1,0 % is permitted.

<sup>d</sup> Where for special reasons, e. g. hot workability for the fabrication of seamless tubes where it is necessary to minimize the deltaferrite content, or with the aim of low magnetic permeability, the maximum Ni content may be increased by the following amounts:  
 0,50 % (m/m): 1.4571.  
 1,00 % (m/m): 1.4306, 1.4406, 1.4429, 1.4434, 1.4436, 1.4438, 1.4541, 1.4550.  
 1,50 % (m/m): 1.4404

<sup>e</sup> Parts made of high sulphur free cutting austenitic steels may not comply with European Directive 94/27 regarding articles in contact with human skin.

<sup>f</sup> Patented steel grade.

Table 5 — Chemical composition (cast analysis) <sup>a</sup> of austenitic-ferritic corrosion resisting steels

Steel designation		% by mass										
Name	Number	C max.	Si	Mn	P max.	S max.	N	Cr	Cu	Mo	Ni	W
X2CrNiN23-4 <sup>†</sup>	1.4362 <sup>†</sup>	0,030	≤ 1,00	≤ 2,00	0,035	0,015	0,05 to 0,20	22,0 to 24,0	0,10 to 0,60	0,10 to 0,60	3,5 to 5,5	-
X2CrNiCuN23-4	1.4655	0,030	≤ 1,00	≤ 2,00	0,035	0,015	0,05 to 0,20	22,0 to 24,0	1,00 to 3,00	0,10 to 0,60	3,5 to 5,5	-
X3CrNiMoN27-5-2	1.4460	0,05	≤ 1,00	≤ 2,00	0,035	0,015 <sup>b</sup>	0,05 to 0,20	25,0 to 28,0	-	1,30 to 2,00	4,5 to 6,5	-
X2CrNiMoN29-7-2 <sup>†</sup>	1.4477 <sup>†</sup>	0,030	≤ 0,50	0,80 to 1,50	0,030	0,015	0,30 to 0,40	28,0 to 30,0	≤ 0,80	1,50 to 2,60	5,8 to 7,5	-
X2CrNiMoN22-5-3 <sup>c</sup>	1.4462 <sup>c</sup>	0,030	≤ 1,00	≤ 2,00	0,035	0,015	0,10 to 0,22	21,0 to 23,0	-	2,50 to 3,5	4,5 to 6,5	-
X2CrNiMoCuN25-6-3	1.4507	0,030	≤ 0,70	≤ 2,00	0,035	0,015	0,20 to 0,30	24,0 to 26,0	1,00 to 2,50	3,0 to 4,0	6,0 to 8,0	-
X2CrNiMoN25-7-4 <sup>†</sup>	1.4410 <sup>†</sup>	0,030	≤ 1,00	≤ 2,00	0,035	0,015	0,24 to 0,35	24,0 to 26,0	-	3,0 to 4,5	6,0 to 8,0	-
X2CrNiMoCuWN25-7-4	1.4501	0,030	≤ 1,00	≤ 1,00	0,035	0,015	0,20 to 0,30	24,0 to 26,0	0,50 to 1,00	3,0 to 4,0	6,0 to 8,0	0,50 to 1,00
X2CrNiMoSi18-5-3	1.4424	0,030	1,40 to 2,00	1,20 to 2,00	0,035	0,015	0,05 to 0,10	18,0 to 19,0	-	2,50 to 3,0	4,5 to 5,2	-

<sup>a</sup> Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

<sup>b</sup> For bars, rods, wire, sections, bright products and the relevant semi-finished products, a maximum content of 0,030 % S applies. Particular ranges of sulphur content may provide improvement of particular properties. For machinability a controlled sulphur content of 0,015 % to 0,030 % is recommended and permitted. For weldability, a controlled sulphur content of 0,008 % to 0,030 % is recommended and permitted. For polishability, a controlled sulphur content of 0,015 % max. is recommended.

<sup>c</sup> By agreement, this grade can be delivered with a Pitting Resistance Equivalent Number (PRE = Cr + 3,3 Mo + 16 N, compare Table C.1) greater than 34.

<sup>†</sup> Patented steel grade.

Table 6 — Chemical composition (cast analysis) <sup>a</sup> of ferritic heat-resisting steels

Steel designation		% by mass							
Name	Number	C	Si	Mn max.	P max.	S max.	Cr	Al	Others
X10CrAlSi7	1.4713	max. 0,12	0,50 to 1,00	1,00	0,040	0,015	6,0 to 8,0	0,50 to 1,00	-
X10CrAlSi13	1.4724	max. 0,12	0,70 to 1,40	1,00	0,040	0,015	12,0 to 14,0	0,70 to 1,20	-
X10CrAlSi18	1.4742	max. 0,12	0,70 to 1,40	1,00	0,040	0,015	17,0 to 19,0	0,70 to 1,20	-
X10CrAlSi25	1.4762	max. 0,12	0,70 to 1,40	1,00	0,040	0,015	23,0 to 26,0	1,20 to 1,70	-
X18CrN28	1.4749	0,15 to 0,20	max. 1,00	1,00	0,040	0,015	26,0 to 29,0	-	N: 0,15 to 0,25
X3CrAlTi18-2	1.4736	max. 0,04	max. 1,00	1,00	0,040	0,015	17,0 to 18,0	1,70 to 2,10	Ti: [4(C+N)+0,2] to 0,80

<sup>a</sup> Elements not listed in the table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

Table 7 — Chemical composition (cast analysis) <sup>a</sup> of austenitic and austenitic-ferritic heat-resisting steels

Steel designation		% by mass								
Name	Number	C	Si	Mn	P max.	S max.	Cr	Ni	N	Others
austenitic heat-resisting steels										
X8CrNiTi18-10	1.4878	≤ 0,10	≤ 1,00	≤ 2,00	0,045	0,015	17,0 to 19,0	9,0 to 12,0	-	Ti: 5xC to 0,80
X15CrNiSi20-12	1.4828	≤ 0,20	1,50 to 2,50	≤ 2,00	0,045	0,015	19,0 to 21,0	11,0 to 13,0	≤ 0,11	-
X9CrNiSiNc21-11-2	1.4835	0,05 to 0,12	1,40 to 2,50	≤ 1,00	0,045	0,015	20,0 to 22,0	10,0 to 12,0	0,12 to 0,20	Ce : 0,03 to 0,08
X12CrNi23-13	1.4833	≤ 0,15	≤ 1,00	≤ 2,00	0,045	0,015	22,0 to 24,0	12,0 to 14,0	≤ 0,11	-
X8CrNi25-21	1.4845	≤ 0,10	≤ 1,50	≤ 2,00	0,045	0,015	24,0 to 26,0	19,0 to 22,0	≤ 0,11	-
X15CrNiSi25-21	1.4841	≤ 0,20	1,50 to 2,50	≤ 2,00	0,045	0,015	24,0 to 26,0	19,0 to 22,0	≤ 0,11	-
X12NiCrSi35-16	1.4864	≤ 0,15	1,00 to 2,00	≤ 2,00	0,045	0,015	15,0 to 17,0	33,0 to 37,0	≤ 0,11	-
X10NiCrAlTi32-21	1.4876	≤ 0,12	≤ 1,00	≤ 2,00	0,030	0,015	19,0 to 23,0	30,0 to 34,0	-	Al : 0,15 to 0,60 Ti : 0,15 to 0,60
X6NiCrNbCe32-27	1.4877	0,04 to 0,08	≤ 0,30	≤ 1,00	0,020	0,010	26,0 to 28,0	31,0 to 33,0	≤ 0,11	Al : ≤ 0,025 Ce : 0,05 to 0,10 Nb : 0,60 to 1,00
X25CrMnNiN25-9-7	1.4872	0,20 to 0,30	≤ 1,00	8,0 to 10,0	0,045	0,015	24,0 to 26,0	6,0 to 8,0	0,20 to 0,40	-
X6CrNiSiNc19-10	1.4818	0,04 to 0,08	1,00 to 2,00	≤ 1,00	0,045	0,015	18,0 to 20,0	9,0 to 11,0	0,12 to 0,20	Ce : 0,03 to 0,08
X6NiCrSiNc35-25 <sup>1)</sup>	1.4854 <sup>1)</sup>	0,04 to 0,08	1,20 to 2,00	≤ 2,00	0,040	0,015	24,0 to 26,0	34,0 to 36,0	0,12 to 0,20	Ce : 0,03 to 0,08
X10NiCrSi35-19	1.4886	≤ 0,15	1,00 to 2,00	≤ 2,00	0,030	0,015	17,0 to 20,0	33,0 to 37,0	≤ 0,11	-
X10NiCrSiNb35-22	1.4887	≤ 0,15	1,00 to 2,00	≤ 2,00	0,030	0,015	20,0 to 23,0	33,0 to 37,0	≤ 0,11	Nb: 1,00 to 1,50
austenitic-ferritic heat-resisting steel										
X15CrNiSi25-4	1.4821	0,10 to 0,20	0,8 to 1,50	≤ 2,00	0,040	0,015	24,5 to 26,5	3,5 to 5,5	≤ 0,11	-
<sup>a</sup> Elements not listed in the table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.										
<sup>1)</sup> Patented steel grade.										

Table 8 — Chemical composition (cast analysis)<sup>a</sup> of martensitic creep-resisting steels

Steel designation		% by mass													
Name	Number	C	Si	Mn	P max.	S max.	N	Al	Cr	Mo	Nb	Ni	V	W	Others
X10CrMoVNb9-1	1.4903	0,08 to 0,12	≤ 0,50	0,30 to 0,60	0,025	0,015	0,030 to 0,070	≤ 0,040	8,0 to 9,5	0,85 to 1,05	0,060 to 0,10	≤ 0,40	0,18 to 0,25	-	-
X11CrMoWVNb9-1-1	1.4905	0,09 to 0,13	0,10 to 0,50	0,30 to 0,60	0,020	0,010	0,050 to 0,090	≤ 0,040	8,5 to 9,5	0,90 to 1,10	0,060 to 0,10	0,10 to 0,40	0,18 to 0,25	0,90 to 1,10	B: 0,000 5 to 0,005 0
X8CrCoNiMo10-6	1.4911	0,05 to 0,12	0,10 to 0,80	0,30 to 1,30	0,025	0,015	≤ 0,035	-	9,8 to 11,2	0,50 to 1,00	0,20 to 0,50	0,20 to 1,20	0,10 to 0,40	≤ 0,70	B: 0,005 to 0,015 Co: 5,0 to 7,0
X19CrMoNbVN11-1	1.4913	0,17 to 0,23	≤ 0,50	0,40 to 0,90	0,025	0,015	0,050 to 0,10	≤ 0,020	10,0 to 11,5	0,50 to 0,80	0,25 to 0,55	0,20 to 0,60	0,10 to 0,30	-	B: ≤ 0,0015
X20CrMoV11-1	1.4922	0,17 to 0,23	≤ 0,40	0,30 to 1,00	0,025	0,015	-	-	10,0 to 12,5	0,80 to 1,20	-	0,30 to 0,80	0,20 to 0,35	-	-
X22CrMoV12-1	1.4923	0,18 to 0,24	≤ 0,50	0,40 to 0,90	0,025	0,015	-	-	11,0 to 12,5	0,80 to 1,20	-	0,30 to 0,80	0,25 to 0,35	-	-
X20CrMoWV12-1	1.4935	0,17 to 0,24	0,10 to 0,50	0,30 to 0,80	0,025	0,015	-	-	11,0 to 12,5	0,80 to 1,20	-	0,30 to 0,80	0,20 to 0,35	0,40 to 0,60	-
X12CrNiMoV12-3	1.4938	0,08 to 0,15	≤ 0,50	0,40 to 0,90	0,025	0,015	0,020 to 0,040	-	11,0 to 12,5	1,50 to 2,00	-	2,00 to 3,00	0,25 to 0,40	-	-

<sup>a</sup> Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.



Table 9 — Chemical composition (cast analysis) <sup>a</sup> of austenitic creep-resisting steels

Steel designation		% by mass														
Name	Number	C	Si	Mn	P max.	S max.	N	Al	Cr	Mo	Nb	Ni	Ti	V	W	Others
X3CrNiMoBN17-13-3	1.4910	≤ 0,04	≤ 0,75	≤ 2,00	0,035	0,015	0,10 to 0,18	-	16,0 to 18,0	2,00 to 3,00	-	12,0 to 14,0	-	-	-	B: 0,001 5 to 0,005 0
X7CrNiNb18-10	1.4912	0,04 to 0,10	≤ 1,00	≤ 2,00	0,045	0,015	-	-	17,0 to 19,0	-	10xC to 1,20	9,0 to 12,0	-	-	-	-
X6CrNiMoB17-12-2	1.4919	0,04 to 0,08	≤ 1,00	≤ 2,00	0,035	0,015	≤ 0,11	-	16,5 to 18,5	2,00 to 2,50	-	10,0 to 13,0	-	-	-	B: 0,001 5 to 0,005 0
X6CrNiTiB18-10	1.4941	0,04 to 0,08	≤ 1,00	≤ 2,00	0,035	0,015	-	-	17,0 to 19,0	-	-	9,0 to 12,0	5xC to 0,80	-	-	B: 0,001 5 to 0,005 0
X6CrNiWNbN16-16	1.4945	0,04 to 0,10	0,30 to 0,60	≤ 1,50	0,035	0,015	0,06 to 0,14	-	15,5 to 17,5	-	10xC to 1,20	15,5 to 17,5	-	-	2,50 to 3,50	-
X6CrNi18-10	1.4948	0,04 to 0,08	≤ 1,00	≤ 2,00	0,035	0,015	≤ 0,11	-	17,0 to 19,0	-	-	8,0 to 11,0	-	-	-	-
X6CrNi23-13	1.4950	0,04 to 0,08	≤ 0,70	≤ 2,00	0,035	0,015	≤ 0,11	-	22,0 to 24,0	-	-	12,0 to 15,0	-	-	-	-
X6CrNi25-20	1.4951	0,04 to 0,08	≤ 0,70	≤ 2,00	0,035	0,015	≤ 0,11	-	24,0 to 26,0	-	-	19,0 to 22,0	-	-	-	-
X5NiCrAlTi31-20	1.4958	0,03 to 0,08	≤ 0,70	≤ 1,50	0,015	0,010	≤ 0,030	0,20 to 0,50	19,0 to 22,0	-	≤ 0,10	30,0 to 32,5	0,20 to 0,50	-	-	Co: ≤ 0,50 Cu: ≤ 0,50
X8NiCrAlTi32-21	1.4959	0,05 to 0,10	≤ 0,70	≤ 1,50	0,015	0,010	≤ 0,030	0,25 to 0,65	19,0 to 22,0	-	-	30,0 to 34,0	0,25 to 0,65	-	-	Co: ≤ 0,50 Cu: ≤ 0,50
X8CrNiNb16-13	1.4961	0,04 to 0,10	0,30 to 0,60	≤ 1,50	0,035	0,015	-	-	15,0 to 17,0	-	10xC to 1,20	12,0 to 14,0	-	-	-	-
X12CrNiWTiB16-13	1.4962	0,07 to 0,15	≤ 0,50	≤ 1,50	0,035	0,015	-	-	15,5 to 17,5	-	-	12,5 to 14,5	0,40 to 0,70	-	2,50 to 3,00	B: 0,001 5 to 0,006 0
X12CrCoNi21-20	1.4971	0,08 to 0,16	≤ 1,00	≤ 2,00	0,035	0,015	0,10 to 0,20	-	20,0 to 22,5	2,50 to 3,5	0,75 to 1,25	19,0 to 21,0	-	-	2,00 to 3,00	Co: 18,5 to 21,0
X6NiCrTiMoVB25-15-2	1.4980	0,03 to 0,08	≤ 1,00	1,00 to 2,00	0,025	0,015	-	≤ 0,35	13,5 to 16,0	1,00 to 1,50	-	24,0 to 27,0	1,90 to 2,30	0,10 to 0,50	-	B: 0,003 0 to 0,010
X8CrNiMoNb16-16	1.4981	0,04 to 0,10	0,30 to 0,60	≤ 1,50	0,035	0,015	-	-	15,5 to 17,5	1,60 to 2,00	10xC to 1,20	15,5 to 17,5	-	-	-	-
X10CrNiMoMnNbVB15-10-1	1.4982	0,07 to 0,13	≤ 1,00	5,5 to 7,0	0,040	0,030	≤ 0,11	-	14,0 to 16,0	0,80 to 1,20	0,75 to 1,25	9,0 to 11,0	-	0,15 to 0,40	-	B:0,003 to 0,009

Table 9 (concluded)

Steel designation		% by mass														
Name	Number	C	Si	Mn	P max.	S max.	N	Al	Cr	Mo	Nb	Ni	Ti	V	W	Others
X6CrNiMoTiB17-13	1.4983	0,04 to 0,08	≤ 0,75	≤ 2,00	0,035	0,015	-	-	16,0 to 18,0	2,00 to 2,50	-	12,0 to 14,0	5xC to 0,80	-	-	B: 0,0015 to 0,0060
X7CrNiMoBNb16-16	1.4986	0,04 to 0,10	0,30 to 0,60	≤ 1,50	0,045	0,030	-	-	15,5 to 17,5	1,60 to 2,00	Nb + Ta: 10xC to 1,20	15,5 to 17,5	-	-	-	B: 0,05 to 0,10
X8CrNiMoVNb16-13	1.4988	0,04 to 0,10	0,30 to 0,60	≤ 1,50	0,035	0,015	0,06 to 0,14	-	15,5 to 17,5	1,10 to 1,50	10xC to 1,20	12,5 to 14,5	-	0,60 to 0,85	-	-
X7CrNiTi18-10	1.4940	0,04 to 0,08	≤ 1,00	≤ 2,00	0,040	0,015	≤ 0,11	-	17,0 to 19,0	-	-	9,0 to 13,0	5x(C+N) to 0,80	-	-	-
X6CrNiMo17-13-2	1.4918	0,04 to 0,08	≤ 0,75	≤ 2,00	0,035	0,015	≤ 0,11	-	16,0 to 18,0	2,00 to 2,50	-	12,0 to 14,0	-	-	-	-

<sup>a</sup> Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the steel.

## Annex A (informative)

### Guidance data on some physical properties

Tables A.1 to A.8 give guidance data on some physical properties for stainless steels.

**Table A.1 — Guidance data on some physical properties of ferritic corrosion resisting steels**

Steel designation		Density	Modulus of elasticity at						Mean coefficient of thermal expansion between 20 °C and					Thermal conductivity at 20 °C	Specific thermal capacity at 20 °C	Electrical resistivity at 20 °C	Magnetiz- able
			20 °C	100 °C	200 °C	300 °C	400 °C	500 °C	100 °C	200 °C	300 °C	400 °C	500 °C				
Name	Number	kg/dm <sup>3</sup>	GPa						$10^{-6} \times K^{-1}$					$\frac{W}{m \cdot K}$	$\frac{J}{kg \cdot K}$	$\frac{\Omega \cdot mm^2}{m}$	
X2CrNi12	1.4003	7,7	220	215	210	205	195	-	10,4	10,8	11,2	11,6	11,9	25	430	0,60	yes
X2CrTi12	1.4512								10,5	11,0	11,5	12,0	12,0	25	460	0,60	
X6CrNiTi12	1.4516								10,5	-	11,5	-	-	30	460	0,60	
X6Cr13	1.4000								10,5	11,0	11,5	12,0	12,0	30	460	0,60	
X6CrAl13	1.4002								10,5	11,0	11,5	12,0	12,0	30	460	0,60	
X2CrTi17	1.4520								10,4	10,8	11,2	11,6	11,9	20	430	0,70	
X6Cr17	1.4016								10,0	10,0	10,5	10,5	11,0	25	460	0,60	
X3CrTi17	1.4510								10,0	10,0	10,5	10,5	11,0	25	460	0,60	
X1CrNb15	1.4595								10,4	10,8	11,2	11,6	11,9	30	460	0,60	
X3CrNb17	1.4511								10,0	10,0	10,5	10,5	11,0	25	460	0,60	
X6CrMo17-1	1.4113								10,0	10,5	10,5	10,5	11,0	25	460	0,70	
X6CrMoS17	1.4105								10,0	10,5	10,5	10,5	11,0	25	460	0,70	
X2CrMoTi17-1	1.4513								10,0	10,5	10,5	10,5	11,0	25	460	0,70	
X2CrMoTi18-2	1.4521								10,4	10,8	11,2	11,6	11,9	23	430	0,80	
X2CrMoTiS18-2	1.4523								10,4	10,8	11,2	11,6	11,9	23	430	0,80	
X6CrNi17-1	1.4017								10,2	-	10,8	-	-	30	460	0,70	
X5CrNiMoTi15-2	1.4589								10,5	11,0	11,5	12,0	12,0	25	460	0,60	
X6CrMoNb17-1	1.4526								11,7	-	12,1	-	-	30	440	0,70	
X2CrNbZr17	1.4590								11	-	11,5	-	-	26	460	0,60	
X2CrTiNb18	1.4509								10,0	10,0	10,5	10,5	-	25	460	0,60	
X2CrMoTi29-4	1.4592	11,5	-	12	-	-	17	440	0,67								

Table A.2 — Guidance data on some physical properties of martensitic and precipitation hardening corrosion resisting steels

Steel designation		Density kg/dm <sup>3</sup>	Modulus of elasticity at					Mean coefficient of thermal expansion between 20 °C and				Thermal conductivity at 20 °C $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C $\frac{\Omega \cdot mm^2}{m}$	Magnetiz- able	
Name	Number		20 °C	100 °C	200 °C	300 °C	400 °C	100 °C	200 °C	300 °C	400 °C					
			GPa					$10^{-6} \times K^{-1}$								
X12Cr13	1.4006	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,60	yes	
X12CrS13	1.4005	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,60		
X15Cr13	1.4024	7,7	216	213	207	200	192	10,5	11,0	11,5	12,0	30	460	0,60		
X20Cr13	1.4021	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,60		
X30Cr13	1.4028	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,65		
X29CrS13	1.4029	7,7	215	212	205	200	190	10,5	-	11,5	-	30	460	0,55		
X39Cr13	1.4031	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,55		
X46Cr13	1.4034	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,55		
X46CrS13	1.4035	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,55		
X38CrMo14	1.4419	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,62		
X55CrMo14	1.4110	7,7	215	212	205	200	190	10,5	11,0	11,5	12,0	30	460	0,62		
X50CrMoV15	1.4116	7,7	215	212	205	200	190	10,5	11,0	11,0	11,5	30	460	0,65		
X70CrMo15	1.4109	7,7	215	212	205	200	190	10,5	11,0	11,0	11,5	30	460	0,65		
X40CrMoVN16-2	1.4123	7,7	195	188	182	177	-	10,4	10,6	10,8	11,1	24	430	0,80		
X14CrMoS17	1.4104	7,7	215	212	205	200	190	10,0	10,5	10,5	10,5	25	460	0,70		
X39CrMo17-1	1.4122	7,7	215	212	205	200	190	10,4	10,8	11,2	11,6	15	430	0,80		
X105CrMo17	1.4125	7,7	215	212	205	200	190	10,4	10,8	11,2	11,6	15	430	0,80		
X90CrMoV18	1.4112	7,7	215	212	205	200	190	10,4	10,8	11,2	11,6	15	430	0,80		
X17CrNi16-2	1.4057	7,7	215	212	205	200	190	10,0	10,5	10,5	10,5	25	460	0,70		
X1CrNiMoCu12-5-2	1.4422	7,7	200	195	185	175	170	10,4	10,8	11,2	11,6	16	450	0,75		
X1CrNiMoCu12-7-3	1.4423	7,7	200	195	185	175	170	10,4	10,8	11,2	11,6	16	450	0,75		
X2CrNiMoV13-5-2	1.4415	7,8	200	195	185	175	170	10,9	-	11,1	-	16	500	0,71		
X3CrNiMo13-4	1.4313	7,7	200	195	185	175	170	10,5	10,9	11,3	11,6	25	430	0,60		
X4CrNiMo16-5-1	1.4418	7,7	200	195	185	175	170	10,3	10,8	11,2	11,6	15	430	0,80		
X1CrNiMoAlTi12-9-2	1.4530	7,7	195	187	178	171	-	10,0	10,3	10,7	11,2	16	500	0,71		
X1CrNiMoAlTi12-10-2	1.4596	7,7	195	187	178	171	-	10,0	10,3	10,7	11,2	16	500	0,71		
X5CrNiCuNb16-4	1.4542	7,8	200	195	185	175	170	10,9	-	11,1	-	16	500	0,71		
X7CrNiAl17-7	1.4568	7,8	200	195	185	175	170	13,0	13,5	14,0	-	16	500	0,80		
X5CrNiMoCuNb14-5	1.4594	7,8	200	195	185	175	170	10,9	-	11,1	-	16	500	0,71		
X5NiCrTiMoVB25-15-2	1.4606	7,9	211	206	200	192	183	16,5	16,8	18,0	17,5	14	460	0,91		no

Table A.3 — Guidance data on some physical properties of austenitic corrosion resisting steels

Steel designation		Density kg/dm <sup>3</sup>	Modulus of elasticity at						Mean coefficient of thermal expansion between 20 °C and					Thermal conductivity at 20 °C $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C $\frac{\Omega \cdot mm^2}{m}$	Magnetiz- able
Name	Number		20 °C	100 °C	200 °C	300 °C	400 °C	500 °C	100 °C	200 °C	300 °C	400 °C	500 °C				
			GPa						$10^{-6} \times K^{-1}$								
X5CrNi17-7	1.4319	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	no <sup>a</sup>
X10CrNi18-8	1.4310	7,9	200	194	186	179	172	165	16,0	17,0	17,0	18,0	18,0	15	500	0,73	
X9CrNi18-9	1.4325	7,9	200	194	186	179	172	165	16,0	17,0	17,0	18,0	18,0	15	500	0,73	
X2CrNi18-7	1.4318	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X2CrNi18-9	1.4307	7,9	200	194	186	179	172	165	16,0	16,5	17,0	18,0	18,0	15	500	0,73	
X2CrNi19-11	1.4306	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X5CrNi19-9	1.4315	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X2CrNi18-10	1.4311	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X5CrNi18-10	1.4301	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X8CrNiS18-9	1.4305	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X6CrNiTi18-10	1.4541	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X6CrNiNb18-10	1.4550	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X4CrNi18-12	1.4303	7,9	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	
X1CrNi25-21	1.4335	7,9	195	190	182	174	166	158	15,8	16,1	16,5	16,9	17,3	14	450	0,85	
X2CrNiMo17-12-2	1.4404	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMoN17-11-2	1.4406	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X5CrNiMo17-12-2	1.4401	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X1CrNiMoN25-22-2	1.4466	8,0	195	190	182	174	166	158	15,7	-	17,0	-	-	14	500	0,80	
X6CrNiMoTi17-12-2	1.4571	8,0	200	194	186	179	172	165	16,5	17,5	18,0	18,5	19,0	15	500	0,75	
X6CrNiMoNb17-12-2	1.4580	8,0	200	194	186	179	172	165	16,5	17,5	18,0	18,5	19,0	15	500	0,75	
X2CrNiMo17-12-3	1.4432	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMoN17-13-3	1.4429	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X3CrNiMo17-13-3	1.4436	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMo18-12-3	1.4449	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMo18-14-3	1.4435	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMoN18-12-4	1.4434	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,75	
X2CrNiMo18-15-4	1.4438	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	14	500	0,85	
X2CrNiMoN17-13-5	1.4439	8,0	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	14	500	0,85	
X1CrNiMoCuN24-22-8	1.4652	8,0	190	184	177	170	164	158	15,0	15,4	15,8	16,2	16,4	8,6	500	0,78	
X1CrNiSi18-15-4	1.4361	7,7	200	194	186	179	172	165	16,5	-	-	-	-	14	-	-	
X11CrNiMnN19-8-6	1.4369	7,9	190	186	179	172	165	158	16,5	17,0	18,0	18,5	19,0	15	500	0,70	
X12CrMnNiN17-7-5	1.4372	7,8	200	194	186	179	172	165	-	-	-	-	-	15	-	0,70	
X2CrMnNiN17-7-5	1.4371	7,8	200	194	186	179	172	165	17,0	17,5	18,0	18,5	-	15	500	0,70	
X12CrMnNiN18-9-5	1.4373	7,8	200	194	186	179	172	165	-	-	-	-	-	15	-	0,70	
X8CrMnNiN18-9-5	1.4374	7,8	199	192	185	170	165	158	16,7	17,3	18,2	18,4	18,6	12	500	0,73	
X8CrMnCuNB17-8-3	1.4597	7,8	200	194	186	179	172	165	16,0	16,5	17,0	17,5	18,0	15	500	0,73	

Table A.3 (concluded)

Steel designation		Density	Modulus of elasticity at						Mean coefficient of thermal expansion between 20 °C and					Thermal conductivity at 20 °C	Specific thermal capacity at 20 °C	Electrical resistivity at 20 °C	Magnetizable
			20 °C	100 °C	200 °C	300 °C	400 °C	500 °C	100 °C	200 °C	300 °C	400 °C	500 °C				
Name	Number	kg/dm <sup>3</sup>	GPa						10 <sup>-6</sup> x K <sup>-1</sup>					$\frac{W}{m \cdot K}$	$\frac{J}{kg \cdot K}$	$\frac{\Omega \cdot mm^2}{m}$	
X3CrNiCu19-9-2	1.4560	7,9	200	194	186	179	172	165	-	-	-	-	-	-	-	-	-
X2CrNiCu19-10	1.4650	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
X6CrNiCuS18-9-2	1.4570	7,9	200	194	186	179	172	165	-	-	-	-	-	-	-	-	-
X3CrNiCu18-9-4	1.4567	7,9	200	194	186	179	172	165	16,7	17,2	17,7	18,1	18,4	-	-	-	-
X3CrNiCuMo17-11-3-2	1.4578	8,0	200	194	186	179	172	165	-	-	-	-	-	-	-	-	-
X1NiCrMoCu31-27-4	1.4563	8,0	195	190	182	174	166	158	15,8	16,1	16,5	16,9	17,3	12	450	1,00	no <sup>a</sup>
X1NiCrMoCu25-20-5	1.4539	8,0	195	190	182	174	166	158	15,8	16,1	16,5	16,9	17,3	12	450	1,00	
X1CrNiMoCuN25-25-5	1.4537	8,1	195	190	182	174	166	158	15,0	-	16,5	-	-	14	500	0,85	
X1CrNiMoCuN20-18-7	1.4547	8,0	195	190	182	174	166	158	16,5	17	17,5	18	18	14	500	0,85	
X2CrNiMoCuS17-10-2	1.4598	8,0	200	194	186	179	172	165	16,5	17,3	17,7	18,1	18,4	14,5	500	0,75	
X1CrNiMoCuNW24-22-6	1.4659	8,2	190	185	179	174	166	158	15,0	15,5	16,0	16,3	16,5	12	450	1,00	
X1NiCrMoCuN25-20-7	1.4529	8,1	195	190	182	174	166	158	15,8	16,1	16,5	16,9	17,3	12	450	1,00	
X2NiCrAlTi32-20	1.4558	8,0	200	195	188	182	175	168	16	16	16	16,5	16,5	12	475	0,99	
X2CrNiMnMoN25-18-6-5	1.4565	8,0	190	186	177	170	165	158	14,5	15,5	16,3	16,8	17,2	12	450	0,92	

<sup>a</sup> Small amounts of ferrite and/or martensite caused by cold deformation will increase the magnetizability.

Table A.4 — Guidance data on some physical properties of austenitic-ferritic corrosion resisting steels

Steel designation		Density kg/dm <sup>3</sup>	Modulus of elasticity at				Mean coefficient of thermal expansion between 20 °C and			Thermal conductivity at 20 °C $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C $\frac{\Omega \cdot mm^2}{m}$	Magnetizable
Name	Number		20 °C	100 °C	200 °C	300 °C	100 °C	200 °C	300 °C				
			GPa				$10^{-6} \times K^{-1}$						
X2CrNiN23-4	1.4362	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	yes
X2CrNiCuN23-4	1.4655	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X3CrNiMoN27-5-2	1.4460	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X2CrNiMoN29-7-2	1.4477	7,7	200	194	186	180	11,5	12,0	12,5	13	470	0,8	
X2CrNiMoN22-5-3	1.4462	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X2CrNiMoCuN25-6-3	1.4507	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X2CrNiMoN25-7-4	1.4410	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X2CrNiMoCuWN25-7-4	1.4501	7,8	200	194	186	180	13,0	13,5	14,0	15	500	0,8	
X2CrNiMoSi18-5-3	1.4424	7,8	200	194	186	180	13,0	13,5	14,0	13	475	0,8	

Table A.5 — Guidance data on some physical properties of ferritic heat-resisting steels

Steel designation		Density  kg/dm <sup>3</sup>	Mean coefficient of thermal expansion between 20 °C and					Thermal conductivity at 20 °C  $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C  $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C  $\frac{\Omega \cdot mm^2}{m}$	Magnetizable
Name	Number		200 °C	400 °C	600 °C	800 °C	1 000 °C				
			$10^{-6} \times K^{-1}$								
X10CrAlSi7	1.4713	7,7	11,5	12,0	12,5	13,0	-	23	450	0,70	yes
X10CrAlSi13	1.4724		10,5	11,5	12,0	12,5	-	21	500	0,75	
X10CrAlSi18	1.4742		10,5	11,5	12,0	12,5	13,5	19	500	0,93	
X10CrAlSi25	1.4762		10,5	11,5	12,0	12,0	13,5	17	500	1,1	
X18CrN28	1.4749		10,0	11,0	11,5	12,0	13,0	17	500	0,70	
X3CrAlTi18-2	1.4736		10,5	10,8	12,0	12,5	13,0	21	500	0,60	



Table A.6 — Guidance data on some physical properties of austenitic and austenitic-ferritic heat-resisting steels

Steel designation		Density kg/dm <sup>3</sup>	Mean coefficient of thermal expansion between 20 °C and					Thermal conductivity at 20 °C $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C $\frac{\Omega \cdot mm^2}{m}$	Magnetizable
Name	Number		200 °C	400 °C	600 °C	800 °C	1 000 °C				
10 <sup>-6</sup> x K <sup>-1</sup>											
austenitic heat-resisting steels											
X8CrNiTi18-10	1.4878	7,9	17,0	18,0	18,5	19,0	-	15	500	0,73	no <sup>a</sup>
X15CrNiSi20-12	1.4828	7,9	16,5	17,5	18,0	18,5	19,5	15	500	0,85	
X9CrNiSiNc21-11-2	1.4835	7,8	17,0	18,0	18,5	19,0	19,5	15	500	0,85	
X12CrNi23-13	1.4833	7,9	16,0	17,5	18,0	18,5	19,5	15	500	0,78	
X8CrNi25-21	1.4845	7,9	15,5	17,0	17,5	18,5	19,0	15	500	0,85	
X15CrNiSi25-21	1.4841	7,9	15,5	17,0	17,5	18,0	19,0	15	500	0,90	
X12NiCrSi35-16	1.4864	8,0	15,0	16,0	17,0	17,5	18,5	12,5	550	1,0	
X10NiCrAlTi32-21	1.4876	8,0	15,0	16,0	17,0	17,5	18,5	12	550	1,0	
X6NiCrNbCe32-27	1.4877	8,0	15,5	16,5	16,5	17,7	18,4	12	450	0,96	
X25CrMnNiN25-9-7	1.4872	7,8	16,5	18,0	18,5	19,0	19,5	14,5	500	0,75	
X6CrNiSiNc19-10	1.4818	7,8	16,5	18,0	18,5	19,0	20,0	15	500	0,85	
X6NiCrSiNc35-25	1.4854	7,9	15,5	16,5	17,0	17,5	18,0	11	450	1,0	
X10NiCrSi35-19	1.4886	8,0	15,5	16,0	17,0	17,7	18,0	12	460	1,0	
X10NiCrSiNb35-22	1.4887	8,0	15,5	16,0	17,0	17,7	18,0	12	460	1,0	
austenitic-ferritic heat-resisting steel											
X15CrNiSi25-4	1.4821	7,7	13,0	13,5	14,0	14,5	15,0	17	500	0,90	yes
<sup>a</sup> Slightly magnetic when cold worked.											

Table A.7 — Guidance data on some physical properties of martensitic creep-resisting steels

Steel Designation		Density kg/dm <sup>3</sup>	Modulus of elasticity at GPa							Mean coefficient of thermal expansion between 20 °C and 10 <sup>-6</sup> x K <sup>-1</sup>						Thermal conductivity at 20 °C $\frac{W}{m \cdot K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \cdot K}$	Electrical resistivity at 20 °C $\frac{\Omega \cdot mm^2}{m}$
Name	Number		20 °C	100 °C	200 °C	300 °C	400 °C	500 °C	600 °C	100 °C	200 °C	300 °C	400 °C	500 °C	600 °C			
X10CrMoVNb9-1	1.4903	7,7	218	213	206	198	190	180	167	10,9	11,3	11,7	12,0	12,3	12,6	26	-	0,50
X11CrMoWVNb9-1-1	1.4905	7,8	218	213	206	198	190	180	167	10,7	11,1	11,5	11,9	12,3	12,6	26	450	0,47
X8CrCoNiMo10-6	1.4911	7,8	215	-	211	206	196	186	-	10,6	11,2	11,4	11,6	11,8	12,0	20	460	0,65
X19CrMoNbVN11-1	1.4913	7,7	216	209	200	290	179	167	127	10,5	11	11,5	12	12,3	12,5	24	460	-
X20CrMoV11-1	1.4922	7,7	216	209	200	290	179	167	127	10,5	10,9	11,3	11,6	12,0	12,2	24	460	0,60
X22CrMoV12-1	1.4923	7,7	216	209	200	290	179	167	127	10,5	11	11,5	12	12,3	12,5	24	460	-
X20CrMoWV12-1	1.4935	7,7	216	209	200	290	179	167	127	10,5	11	11,5	12	12,3	12,5	24	460	-
X12CrNiMoV12-3	1.4938	7,8	216	209	200	290	179	167	127	10,8	11	11,3	11,6	11,9	12,1	30	460	0,60

Table A.8 — Guidance data on some physical properties of austenitic creep-resisting steels

Steel Designation		Density kg/dm <sup>3</sup>	Modulus of elasticity at											Mean coefficient of thermal expansion between 20 °C and										Thermal conductivity at 20 °C $\frac{W}{m \times K}$	Specific thermal capacity at 20 °C $\frac{J}{kg \times K}$	Electrical resistivity at 20 °C $\frac{\Omega \times mm^2}{m}$
Name	Number		20 °C	100 °C	200 °C	300 °C	400 °C	500 °C	600 °C	700 °C	800 °C	900 °C	1000 °C	100 °C	200 °C	300 °C	400 °C	500 °C	600 °C	700 °C	800 °C	900 °C	1000 °C			
			GPa											$10^{-6} \times K^{-1}$												
X3CrNiMoBN17-13-3	1.4910	8,0	200	190	185	175	170	160	155	145	140	135	125	16,3	16,9	17,3	17,8	18,2	18,5	18,7	-	-	-	16	450	0,77
X7CrNiNb18-10	1.4912	7,9	200	194	186	179	172	165	155	-	-	-	-	16,0	16,5	17,0	17,5	18,0	18,5	-	-	-	-	15	500	0,73
X6CrNiMoB17-12-2	1.4919	8,0	196	192	186	181	174	165	157	-	-	-	-	16,3	16,9	17,3	-	18,2	18,5	-	-	-	-	16	450	0,77
X6CrNiTiB18-10	1.4941	7,9	200	190	185	175	170	160	155	145	140	135	125	16,3	16,9	17,3	17,8	18,2	18,5	18,7	-	-	-	17	450	0,71
X6CrNiWNB16-16	1.4945	8,0	196	192	186	181	174	165	157	-	-	-	-	10,5	10,9	11,3	11,6	12,0	12,2	-	-	-	-	14	440	0,60
X6CrNi18-10	1.4948	7,9	200	190	185	175	170	160	155	145	140	135	125	16,3	16,9	17,3	17,8	18,2	18,5	18,7	-	-	-	17	450	0,71
X6CrNi23-13	1.4950	7,9	200	190	185	175	170	160	155	145	140	135	125	-	16,0	16,8	17,5	17,8	18,0	18,3	18,5	19,0	19,5	15	500	0,78
X6CrNi25-20	1.4951	7,9	200	190	185	175	170	160	155	145	140	135	125	-	15,5	16,3	17,0	17,3	17,5	18,0	18,5	18,8	19,0	15	500	0,85
X5NiCrAlTi31-20	1.4958	8,0	200	190	185	175	170	160	155	145	140	135	125	15,4	16,0	16,5	16,8	17,2	17,5	17,9	18,3	18,6	19,0	12	460	0,99
X8NiCrAlTi32-21	1.4959	8,0	200	190	185	175	170	160	155	145	140	135	125	15,4	16,0	16,5	16,8	17,2	17,5	17,9	18,3	18,6	19,0	12	460	0,99
X8CrNiNb16-13	1.4961	7,9	200	190	185	175	170	160	155	145	140	135	125	16,3	16,9	17,3	17,8	18,2	18,5	18,7	-	-	-	16	450	0,78
X12CrNiWTiB16-13	1.4962	8,0	196	191	182	175	167	159	151	-	-	-	-	15,6	16,8	17,5	18,0	18,3	18,6	-	-	-	-	14	500	0,74
X12CrCoNi21-20	1.4971	8,3	200	195	190	185	178	170	160	-	-	-	-	14,2	14,6	15,0	15,5	15,9	16,4	-	-	-	-	11,6	-	-
X6NiCrTiMoVB25-15-2	1.4980	8,0	196	192	186	180	172	167	157	-	-	-	-	17,0	17,5	18,7	18,0	18,2	18,5	-	-	-	-	-	-	-
X8CrNiMoNb16-16	1.4981	8,0	198	192	183	175	167	159	150	-	-	-	-	16,3	16,9	17,3	17,8	18,2	18,5	-	-	-	-	16	450	0,77
X10CrNiMoMnNbVB15-10-1	1.4982	8,0	207	201	193	184	175	165	158	-	-	-	-	15,7	16,8	17,7	18,3	18,6	19,0	-	-	-	-	12,5	480	0,74
X6CrNiMoTiB17-13	1.4983	8,0	200	190	185	175	170	160	155	-	-	-	-	-	17,0	-	18,0	-	-	-	-	-	-	15	500	0,74
X7CrNiMoBNb16-16	1.4986	7,9	196	192	186	181	174	165	157	-	-	-	-	16,6	17,7	17,9	17,9	17,9	18,1	-	-	-	-	15	460	-
X8CrNiMoVNb16-13	1.4988	8,0	198	192	183	175	167	159	150	-	-	-	-	16,3	16,9	17,3	17,8	18,2	18,5	-	-	-	-	15	450	0,79
X7CrNiTi18-10	1.4940	7,9	200	194	186	179	172	165	155	-	-	-	-	16,0	16,5	17,0	17,5	18,0	18,5	-	-	-	-	15	500	0,73
X6CrNiMo17-13-2	1.4918	8,0	200	194	186	179	172	165	155	-	-	-	-	16,0	16,5	17,0	17,5	18,0	18,5	-	-	-	-	15	500	0,75

## Annex B (informative)

### Classification of stainless steel grades

#### B.1 General

Stainless steels are classified according to 3 principles:

- use properties, to produce material standards;
- microstructure, to produce tables in the standards;
- significant alloying elements, to sort grades in the tables.

They may be further classified according to availability into standard grades and special grades. Special grades are intended for a particular use and with limited availability. Some alloy steels within the stainless steel definition are classified according to their use function as tool or valve steels.

#### B.2 Classification by use properties

##### B.2.1 Corrosion resisting

A corrosion resisting steel is a steel with a good resistance to uniform or local attack from the environment. The protection is provided by a minimum content of 10,5 % Cr through a spontaneously formed chromium oxide film. The environment may be atmospheric at ambient temperature (indoor, rural, urban, industrial, marine) or a solution giving electrochemical conditions.

EN grades are given steel numbers (EN 10027-2) in the groups:

- 1.40xx for grades with < 2,5% Ni, without Mo, without special additions;
- 1.41xx for grades with < 2,5% Ni, with Mo, without special additions;
- 1.43xx for grades with  $\geq$  2,5% Ni, without Mo, without special additions;
- 1.44xx for grades with  $\geq$  2,5% Ni, with Mo, without special additions;
- 1.45xx and 1.46xx for grades with special additions, such as Ti, Nb or Cu.

##### B.2.2 Heat resisting

A heat resisting steel is a steel, mainly ferritic or austenitic, with a good resistance to oxidation and the effects of hot gases and combustion products at temperatures higher than 550 °C. In oxidizing atmospheres a protective oxide layer is formed by chromium, silicon and aluminium on the steel surface. This oxide also reduces the attack from sulphur. In a reducing atmosphere, where no oxide is formed, an increased nickel content will reduce carbon and nitrogen pickup, but increases the susceptibility to sulphur attack.

EN grades are given steel numbers in the groups:

- 1.47xx for grades with < 2,5% Ni;

1.48xx for grades with  $\geq 2,5\%$  Ni.

### B.2.3 Creep resisting

A creep resisting steel is a steel, mainly martensitic and austenitic, with good resistance to deformation under mechanical long-time stressing at temperatures above 500 °C. Several austenitic grades are variants of grades in B.2.1 and B.2.2 with specified minimum carbon content.

EN grades are given steel numbers in the group 1.49xx.

## B.3 Classification by microstructure

### B.3.1 Ferritic

Ferrite (alpha-iron,  $\alpha$ -Fe) has a body centred cubic (bcc) atomic packing. It is magnetic, and is brittle below a characteristic transition temperature. Delta-ferrite ( $\delta$ ) is a residual bcc structure from the solidification process and has similar characteristics.

Ferritic steels are annealed at temperatures 750 - 950 °C, to avoid the formation of austenite. Heat treatments at higher temperatures (typical example: heat affected zones in welds) may result in the formation of austenite, which transforms to martensite on cooling, and may also cause embrittlement due to grain coarsening. These effects are reduced by stabilisation of the C and N contents with Ti, Nb or Zr.

As a rule, ferritic steels have a poor weldability due to their sensitivity to intergranular corrosion and embrittlement in the heat affected zone.

In the ASTM standards, the ferritic grades are classified in the 400 series.

### B.3.2 Martensitic

Martensite is formed from austenite during heat treatment or by cold working. It has a high strength and is magnetic.

Above 900 °C to 1 000 °C these steels have an austenitic structure with high solubility for carbon. Upon cooling the austenite transforms to a supersaturated solution of carbon in a quadratic body centred  $\alpha'$ -matrix, i.e. martensite, which is stable down to ambient temperature.

If the structure contains a high amount of ferrite the steels are called "*martensitic-ferritic*" or "*semi-ferritic*". Steel grade examples are grades 1.4005 and 1.4006.

Traditional martensitic steels have high carbon contents in the range 0,08 % to 1 %. They are air hardening on cooling, but their mechanical strength may be increased by a quenching heat treatment. The type of cooling (in air, oil or water) is adapted for each grade. The ductility is improved by a tempering treatment before use. With carbon contents  $> 0,20\%$ , they are difficult to weld.

Martensitic steels are also made with a low carbon content (max. 0,06 %) and 3 % to 6 % Ni. These steels have a balanced composition that promotes stable austenite after hardening and tempering and are called "*martensitic-austenitic*" or "*nickel martensitic*". These steels have a relatively good weldability. Examples are grades 1.4313 and 1.4418.

The low carbon type has been further developed to "*supermartensitic*" steels. Typical compositions are 11 % to 13 % Cr, 2 % to 6 % Ni, 0 to 3 % Mo and max. 0,030 % C and N. Their high strength is combined with good impact strength and good weldability. An example is 1.4415 (X2CrNiMoV13-5-2).

In the ASTM standards, the martensitic grades are classified in the 400 series.

### B.3.3 Precipitation hardening

After solution annealing and quenching, the precipitation of intermetallic compounds, carbides, nitrides or copper phase from the martensitic structure gives an increased strength.

The specific heat treatment conditions shall be adjusted depending on the desired level of mechanical properties and the data provided by the manufacturers.

Examples are grades 1.4568, 1.4542 and 1.4594.

### B.3.4 Austenitic

Austenite (gamma-iron,  $\gamma$  Fe) has a face centered cubic (fcc) atomic packing. It is not magnetic, and is ductile over a wide temperature range, from cryogenic to creep temperatures. It does not display brittle fracture. The tensile strength is high at low temperatures. By coldforming it may be workhardened to high strength levels.

Austenitic grades are solution annealed within the range 1 000 °C to 1 200 °C. Austenite does not harden from heat treatment. Austenite formers like Ni, C and N promote the austenitic structure, whereas ferrite formers like Cr, Mo and Si promote a ferritic structure. Conventional austenitic grades may contain traces of delta ferrite, for improved weldability. Alloying with interstitial elements, particularly N, will increase the strength.

The stability of the austenitic structure depends on the amount of alloying elements. Grades with alloy content on the low side may transform to martensite during plastic deformation and/or by cooling to low temperature. They are called "*metastable austenitic*". Typical examples are grades 1.4310 and 1.4318.

Ferrite traces and high chromium and molybdenum contents may promote precipitation of sigma phase ( $\sigma$ ) which is brittle. The critical temperature range for precipitation of this and other intermetallic phases is 600 °C to 900 °C.

Stable austenitic grades without any ferrite are called "*fully austenitic*" and may require special care in hot forming and welding. Typical examples are grades 1.4466 and 1.4539.

Grades with excellent corrosion resistance in aggressive environments due to high chromium, molybdenum and nitrogen contents may be called "*superaustenitic*". Typical examples are grades 1.4547 and 1.4652

The metallic materials grouping system in CR ISO 15608 defines a separate austenitic steel group 8.2, with typical chromium contents over 19 %. This group contains all superaustenitic and most fully austenitic grades.

In the ASTM standards, the austenitic grades with manganese contents equal to or lower than 2 % are classified in the 300 series.

### B.3.5 Austenitic-ferritic (Duplex)

These steels have a well-balanced two-phase structure, with ferrite content between 30 % and 50 %. Strength properties are higher than for austenitic steels hence high power is required for cold deformation. These steels have a good resistance to stress corrosion cracking.

Sigma phase, and other phases that may reduce toughness and corrosion resistance, can be formed rapidly in the range 600 °C to 900 °C, primarily from the ferrite. Hot forming is therefore to be performed well above these temperatures and followed by rapid cooling. Welds should be cooled rapidly through this range.

The metallic materials grouping system in CR ISO 15608 defines a separate austenitic-ferritic steel group 10.2, with typical chromium contents over 24 %. This group will contain "*superduplex*" grades with high chromium, molybdenum and nitrogen contents. Typical examples are grades 1.4410, 1.4507 or 1.4501.

In the ASTM standards, the austenitic-ferritic grades are classified in the 300 series.

## B.4 Classification by significant alloying elements

### B.4.1 Chromium and Nickel

Chromium and Nickel are the main alloying elements in stainless steel, and give the basic sorting order in EN standards. "*Cr-steel*" is a traditional term for ferritic grades, whereas "*CrNi-steel*" may be used for austenitic grades.

### B.4.2 Molybdenum

Molybdenum improves the corrosion resistance, especially against chloride induced pitting. It is detrimental in oxidizing acids, like nitric acid, and in oxidizing atmospheres at high temperature.

Austenitic grades with over 2 % Mo may be called "*CrNiMo-steel*". They were earlier called "*acid resisting*", due to their resistance in the acid sulphite pulping process.

### B.4.3 Manganese

Manganese is added as a substitute for nickel as an austenite former and to increase the solubility of nitrogen. The metallic materials grouping system in CR ISO 15608 defines a separate austenitic steel group 8.3, with manganese contents 2 % to 9 %.

In the ASTM standards, the austenitic grades with manganese contents higher than 2 % are classified in the 200 series.

### B.4.4 Low carbon

Chromium carbides may precipitate in the grain boundaries during slow cooling after heat treatment or welding, and cause intergranular attack in contact with corrosive environments. The critical temperature range is 600 °C to 800 °C. The modern method to avoid intergranular corrosion is to make steels with  $\leq 0,030$  % carbon, so called LC-steels (Low Carbon), in which case all of the carbon remains in solid solution and does not combine with chromium to form chromium-carbide precipitates. The traditional method is described in B.4.6.

### B.4.5 Nitrogen

Nitrogen, being a strong austenite stabilizing element, is added as a substitute for nickel as an austenite former and to increase strength as well as the resistance to pitting corrosion.

### B.4.6 Stabilization

Addition of titanium, niobium and/or zirconium prevents the precipitation of chromium carbides following heat treatment and/or welding processes. Stabilization was the preferred method up to the 1960's, when technological advances enabled low carbon grades to be made cheap and reliable. Stabilized grades display good strength properties up to about 600 °C.

### B.4.7 Sulphur

Sulphur promotes chip breaking in machining operations and improves machinability considerably. Free cutting grades with 0,15 % to 0,35% S are thus available with ferritic, martensitic and austenitic microstructure. The addition of sulphur is however detrimental to impact strength and corrosion resistance.

## Annex C (informative)

### Empirical formulae for steel grade classification by microstructure

The formulae given in Table C.1 are used for characterisation of grades and classification into groups. They may be updated and harmonised with other formulae in use. The traditional groups for Ferrite, Martensite and Austenite are complemented with transition groups marked in bold. The basis is the average chemical composition for the grade, i.e. (min+max/2). The steel groups are similar to the grouping of metallic materials in CR ISO 15608.

The formulae may also be used in steel manufacturing for statistical process control, and for optimisation of properties within composition limits.

**Table C.1 — Empirical formulae for steel grade classification by microstructure**

Microstructure characteristics	Formulae and parameters	Range of application	
<b>FM</b> Ferrite - Martensite- region in Schaeffler/de Long diagram	$FM = (A - 1,2)/(F - 8)$ for $F = \min 8$ where: $F = 1,5Si + Cr + Mo + 2Ti + 0,5Nb$ $A = 30C + 0,5Mn + 30N + Ni + 0,5Cu + 0,5Co$	Fer	Ferritic when: $FM = 0,00 - 0,30$
		Martensitic	<b>Ferritic-Martensitic</b> when: $FM = 0,30 - 1,0$
			Martensitic when: $FM = 1,0 - 4$
<b>MS</b> Ferrite - Martensite transform (1)	$MS = 540 - 497C - 6,3Mn - 10,8Cr - 36,3Ni - 46,6Mo$		Martensitic when: $MS = 100 - 300$
<b>MNA</b> Martensite Number based on Md30 (2)	$MNA = 551 - 462(C+N) - 9,2Si - 8,1Mn - 13,7Cr - 29(Ni+Cu) - 18,5Mo - 68Nb$		<b>Austenitic-Martensitic</b> when: $MNA = 100 - 300$
<b>MNK</b> Martensite Number based on WRC-1992 diagram (4)	$MNK = 25 - F - 0,90A$ for $Mn = \max 2,4 \%$ $MNK = 21 - 0,90F - A$ for $Mn = 2,5 - 6,9 \%$ $MNK = 13 - 0,42F - 1,3A$ for $Mn = \min 7,0 \%$ where: $F = Cr + Mo + 2Ti + 0,7Nb$ $A = 35C + 20N + Ni + 0,25Cu$	Austenitic	<b>Metastable austenitic</b> when: $MNA = 0 - 100$ or $MNK = (-2) - 0$
			Austenitic when: $MS = (-1000) - (-10)$
<b>MS</b> Austenite - Martensite transform (3)	$MS = 502 - 810C - 13Mn - 1230N - 12Cr - 30Ni - 46Mo - 54Cu$		Fully austenitic when: $SM = (-30) - (-4)$
<b>SM</b> Solidification Mode based on WRC-1992 diagram (4)	$SM = F - 1,3A - 2,0$ where: $F = Cr + Mo + 2Ti + 0,7Nb$ $A = 35C + 20N + Ni + 0,25Cu$		Austenitic when: $FNA = (-40) - 20$
<b>FNA</b> Ferrite Number based on complemented Schaeffler/de Long diagram (5)	$FNA = 3,34F - 2,46A - 28,6$ for $FNA = \max 5,9$ $FNA = 4,44F - 3,39A - 38,4$ for $FNA = 6,0 - 11,9$ $FNA = 4,06F - 3,23A - 32,2$ for $FNA = \min 12$ where: $F = 1,5Si + Cr + Mo + 2Ti + 0,5Nb$ $A = 30C + 0,5Mn + 30N + Ni + 0,5Cu + 0,5Co$	Duplex	<b>Austenitic-Ferritic (Duplex)</b> when: $FNA = 30 - 50$ or $SM = 8 - 15$
			Sensitive to formation of IMP when: $IMP = 4 - 10$
<b>IMP</b> Intermetallic phases based on FNA equivalents and (3)	$IMP = F - 0,23A - 20,2$ for $A = \min 8,7$ $IMP = F + 1,25A - 32,8$ for $A = \max 8,6$		Resistant when: $PRE = 40 - 60$
<b>PRE</b> Pitting Resistance Equivalent (6)	$PRE = Cr + 3,3Mo + 16N$ most common formula for Super-austenitic/duplex/ferritic $PRE = Cr + 3,3Mo + 30N$ also for austenitic steels with Mo > 3%		
(1) Walker, Gooch. 1986	(4) Kotecki, Siewert. WRC 1992. Kotecki 2000		
(2) Angel 1954. Nohara 1977	(5) ASME Sect III Div 1 NB-2433. 1992		
(3) SINTEF Welding handbook. 1997	(6) Herbsleb (30N) 1982. Truman (16N) 1987		



## Annex D (informative)

### Matrix to show which steels are included in which standards

**Table D.1 — Matrix to show which steels are included in which standards (current at June 2004)**

Steel designation Name	Number	Steels listed in EN 10088-1 and specified in																	
		EN 10028-7	EN 10088-2	EN 10088-3	EN 10095	EN 10151	EN 10216-5	EN 10217-7	EN 10222-5	EN 10250-4	EN 10263-5	EN 10264-4	EN 10269	EN 10270-3	EN 10272	EN 10296-2	EN 10297-2	EN 10302	EN 10312
<b>ferritic corrosion resisting steels</b>																			
X2CrNi12	1.4003	x	x	x											x	x			
X2CrTi12	1.4512		x		x											x	x		
X6CrNiTi12	1.4516	x	x																
X6Cr13	1.4000		x	x	x														
X6CrAl13	1.4002		x						x								x		
X2CrTi17	1.4520	x	x	x															
X6Cr17	1.4016		x	x	x	x				x	x						x	x	
X3CrTi17	1.4510	x	x		x												x	x	
X1CrNb15	1.4595		x																x
X3CrNb17	1.4511		x	x															x
X6CrMo17-1	1.4113		x	x							x								
X6CrMoS17	1.4105			x															
X2CrMoTi17-1	1.4513		x																
X2CrMoTi18-2	1.4521	x	x														x		x
X2CrMoTiS18-2	1.4523			x															
X6CrNi17-1	1.4017		x																
X5CrNiMoTi15-2	1.4589		x																
X6CrMoNb17-1	1.4526		x	x													x		
X2CrNbZr17	1.4590		x		x														
X2CrTiNb18	1.4509	x	x	x	x												x		
X2CrMoTi29-4	1.4592		x																
<b>martensitic and precipitation hardening corrosion resisting steels</b>																			
X12Cr13	1.4006		x	x	x					x	x				x			x	
X12CrS13	1.4005			x															
X15Cr13	1.4024		x	x															
X20Cr13	1.4021		x	x		x				x									
X30Cr13	1.4028		x	x		x				x									
X29CrS13	1.4029			x															
X39Cr13	1.4031		x	x		x													
X46Cr13	1.4034		x	x															
X46CrS13	1.4035			x															
X38CrMo14	1.4419		x	x															
X55CrMo14	1.4110		x	x															
X50CrMoV15	1.4116		x	x															

Table D.1 (continued)

Steel designation		steels listed in EN 10088-1 and specified in																	
Name	Number	EN 10028-7	EN 10088-2	EN 10088-3	EN 10095	EN 10151	EN 10216-5	EN 10217-7	EN 10222-5	EN 10250-4	EN 10263-5	EN 10264-4	EN 10269	EN 10270-3	EN 10272	EN 10296-2	EN 10297-2	EN 10302	EN 10312
X70CrMo15	1.4109			x															
X40CrMoVN16-2	1.4123			x															
X14CrMoS17	1.4104			x															
X39CrMo17-1	1.4122		x	x															
X105CrMo17	1.4125			x															
X90CrMoV18	1.4112			x															
X17CrNi16-2	1.4057			x						x					x				
X1CrNiMoCu12-5-2	1.4422		x																
X1CrNiMoCu12-7-3	1.4423		x																
X2CrNiMoV13-5-2	1.4415			x															
X3CrNiMo13-4	1.4313	x	x	x					x	x					x				
X4CrNiMo16-5-1	1.4418	x	x	x						x					x				
X1CrNiMoAlTi12-9-2	1.4530			x															
X1CrNiMoAlTi12-10-2	1.4596			x															
X5CrNiCuNb16-4	1.4542		x	x						x									
X7CrNiAl17-7	1.4568		x	x		x									x				
X5CrNiMoCuNb14-5	1.4594			x															
X5NiCrTiMoVB25-15-2	1.4606			x															
<b>austenitic corrosion resisting steels</b>																			
X5CrNi17-7	1.4319		x	x															
X10CrNi18-8	1.4310		x	x		x								x					
X9CrNi18-9	1.4325			x															
X2CrNiN18-7	1.4318	x	x																
X2CrNi18-9	1.4307	x	x	x			x	x	x	x			x		x	x	x		
X2CrNi19-11	1.4306	x	x	x			x	x		x	x				x	x	x		
X5CrNi19-9	1.4315	x	x	x															
X2CrNiN18-10	1.4311	x	x	x			x	x	x	x					x	x	x		
X5CrNi18-10	1.4301	x	x	x	x	x	x	x	x	x	x	x	x		x	x	x		x
X8CrNiS18-9	1.4305		x	x															x
X6CrNiTi18-10	1.4541	x	x	x	x		x	x	x	x	x				x	x	x		x
X6CrNiNb18-10	1.4550	x	x	x			x	x	x	x					x	x	x		
X4CrNi18-12	1.4303		x	x									x	x	x				
X1CrNi25-21	1.4335	x	x				x												x
X2CrNiMo17-12-2	1.4404	x	x	x			x	x	x	x			x		x	x	x		x
X2CrNiMoN17-11-2	1.4406	x	x	x					x	x					x				x
X5CrNiMo17-12-2	1.4401	x	x	x		x	x	x	x	x	x	x	x	x	x	x	x		x
X1CrNiMoN25-22-2	1.4466	x	x	x			x												x
X6CrNiMoTi17-12-2	1.4571	x	x	x			x	x	x	x	x				x	x	x		x
X6CrNiMoNb17-12-2	1.4580	x	x	x			x								x				x
X2CrNiMo17-12-3	1.4432	x	x	x				x	x		x				x	x			
X2CrNiMoN17-13-3	1.4429	x	x	x			x	x	x	x	x		x		x	x	x		
X3CrNiMo17-13-3	1.4436	x	x	x			x	x	x	x	x				x	x	x		
X3CrNiMo18-12-3	1.4449								x										
X2CrNiMo18-14-3	1.4435	x	x	x			x	x	x	x					x	x	x		x
X2CrNiMoN18-12-4	1.4434	x	x																
X2CrNiMo18-15-4	1.4438	x	x	x				x											

Table D.1 (continued)

Steel designation Name	Number	steels listed in EN 10088-1 and specified in																	
		EN 10028-7	EN 10088-2	EN 10088-3	EN 10095	EN 10151	EN 10216-5	EN 10217-7	EN 10222-5	EN 10250-4	EN 10263-5	EN 10264-4	EN 10269	EN 10270-3	EN 10272	EN 10296-2	EN 10297-2	EN 10302	EN 10312
X2CrNiMoN17-13-5	1.4439	x	x	x			x	x							x	x	x		x
X1CrNiMoCuN24-22-8 <sup>1)</sup>	1.4652 <sup>1)</sup>		x	x															
X1CrNiSi18-15-4	1.4361		x	x															
X11CrNiMnN19-8-6	1.4369		x	x		x													
X12CrMnNiN17-7-5	1.4372		x	x		x													
X2CrMnNiN17-7-5	1.4371		x																
X12CrMnNiN18-9-5	1.4373		x																
X8CrMnNiN18-9-5	1.4374			x															
X8CrMnCuNB17-8-3	1.4597		x	x															
X3CrNiCu19-9-2	1.4560			x							x								
X2CrNiCu19-10	1.4650							x											
X6CrNiCuS18-9-2	1.4570			x															
X3CrNiCu18-9-4	1.4567			x															
X3CrNiCuMo17-11-3-2	1.4578			x															
X1NiCrMoCu31-27-4	1.4563	x	x	x			x	x							x		x		
X1NiCrMoCu25-20-5	1.4539	x	x	x			x	x		x					x		x		x
X1CrNiMoCuN25-25-5	1.4537	x	x	x															
X1CrNiMoCuN20-18-7	1.4547	x	x	x			x	x		x					x		x		
X2CrNiMoCuS17-10-2	1.4598			x															
X1CrNiMoCuNW24-22-6	1.4659		x	x															
X1NiCrMoCuN25-20-7	1.4529	x	x	x			x	x		x					x		x		x
X2NiCrAlTi32-20	1.4558						x										x		
X2CrNiMnMoN25-18-6-5	1.4565		x	x															
<b>austenitic-ferritic corrosion resisting steels</b>																			
X2CrNiN23-4 <sup>1)</sup>	1.4362 <sup>1)</sup>	x	x	x	x		x	x		x					x	x	x		
X2CrNiCuN23-4	1.4655		x																
X3CrNiMoN27-5-2	1.4460			x						x							x		
X2CrNiMoN29-7-2 <sup>1)</sup>	1.4477 <sup>1)</sup>		x	x															
X2CrNiMoN22-5-3	1.4462	x	x	x			x	x	x	x	x				x	x	x		x
X2CrNiMoCuN25-6-3	1.4507	x	x	x			x			x					x		x		
X2CrNiMoN25-7-4 <sup>1)</sup>	1.4410 <sup>1)</sup>	x	x	x			x	x	x	x					x	x	x		
X2CrNiMoCuWN25-7-4	1.4501	x	x	x			x	x		x					x		x		
X2CrNiMoSi18-5-3	1.4424		x	x			x										x		
<b>ferritic heat-resisting steels</b>																			
X10CrAlSi7	1.4713				x														
X10CrAlSi13	1.4724				x														
X10CrAlSi18	1.4742				x														
X10CrAlSi25	1.4762				x														
X18CrN28	1.4749				x														
X3CrAlTi18-2	1.4736				x														
<b>austenitic heat-resisting steels</b>																			
X8CrNiTi18-10	1.4878				x														
X15CrNiSi20-12	1.4828				x														
X9CrNiSiN21-11-2	1.4835				x														
X12CrNi23-13	1.4833				x														
X8CrNi25-21	1.4845				x														

Table D.1 (concluded)

Steel designation Name	Number	steels listed in EN 10088-1 and specified in																	
		EN 10028-7	EN 10088-2	EN 10088-3	EN 10095	EN 10151	EN 10216-5	EN 10217-7	EN 10222-5	EN 10250-4	EN 10263-5	EN 10264-4	EN 10269	EN 10270-3	EN 10272	EN 10296-2	EN 10297-2	EN 10302	EN 10312
X15CrNiSi25-21	1.4841				x							x							
X12NiCrSi35-16	1.4864				x														
X10NiCrAlTi32-21	1.4876				x														
X6NiCrNbCe32-27	1.4877				x														
X25CrMnNiN25-9-7	1.4872				x														
X6CrNiSiN25-9-7	1.4818				x														
X6NiCrSiN25-9-7 <sup>1)</sup>	1.4854 <sup>1)</sup>				x														
X10NiCrSi35-19	1.4886				x														
X10NiCrSiNb35-22	1.4887				x														
<b>austenitic-ferritic heat-resisting steel</b>																			
X15CrNiSi25-4	1.4821				x														
<b>martensitic creep-resisting steels</b>																			
X10CrMoVNb9-1	1.4903																		x
X11CrMoWVNb9-1-1	1.4905																		x
X8CrCoNiMo10-6	1.4911																		x
X19CrMoNbVN11-1	1.4913												x						x
X20CrMoV11-1	1.4922																		x
X22CrMoV12-1	1.4923																		x
X20CrMoWV12-1	1.4935																		x
X12CrNiMoV12-3	1.4938																		x
<b>austenitic creep-resisting steels</b>																			
X3CrNiMoBN17-13-3	1.4910	x						x		x				x					x
X7CrNiNb18-10	1.4912							x		x									
X6CrNiMoB17-12-2	1.4919																		x
X6CrNiTiB18-10	1.4941	x			x			x		x									x
X6CrNiWNB16-16	1.4945																		x
X6CrNi18-10	1.4948	x			x			x		x									
X6CrNi23-13	1.4950	x			x														
X6CrNi25-20	1.4951	x			x														
X5NiCrAlTi31-20	1.4958	x						x											x
X8NiCrAlTi32-21	1.4959	x						x											x
X8CrNiNb16-13	1.4961	x						x											x
X12CrNiWTiB16-13	1.4962																		x
X12CrCoNi21-20	1.4971																		x
X6NiCrTiMoVB25-15-2	1.4980																		x
X8CrNiMoNb16-16	1.4981							x											x
X10CrNiMoMnNbVB15-10-1	1.4982							x											x
X6CrNiMoTiB17-13	1.4983																		x
X7CrNiMoBNb16-16	1.4986																		x
X8CrNiMoVNb16-13	1.4988							x											x
X7CrNiTi18-10	1.4940							x											
X6CrNiMo17-13-2	1.4918							x											

<sup>1)</sup> Patented steel grade.

## Annex E (informative)

### Chemical composition of nickel and cobalt alloys listed in EN 10095, EN 10269 and EN 10302

The chemical composition of nickel and cobalt alloys listed in EN 10095, EN 10269 and EN 10302 are given in Tables E.1 and E.2.

**Table E.1 — Chemical composition (cast analysis) <sup>a</sup> of nickel alloys listed in EN 10095**

Alloy designation		% by mass															
Name	Number	C	Mn max.	Si	P max.	S max.	Ni	Cr	Co	Fe	Mo	Al	Ti	Cu max.	Nb+Ta	B max.	Ce
NiCr15Fe	2.4816	0,05 to 0,10	1,00	≤ 0,50	0,020	0,015	≥ 72,0	14,0 to 17,0	<sup>b</sup>	6,0 to 10,0	-	≤ 0,30	≤ 0,30	0,50	-	-	-
NiCr20Ti	2.4951	0,08 to 0,15	1,00	≤ 1,00	0,020	0,015	Rem.	18,0 to 21,0	≤ 5,0	≤ 5,0	-	≤ 0,30	0,20 to 0,60	0,50	-	-	-
NiCr22Mo9Nb	2.4856	0,03 to 0,10	0,50	≤ 0,50	0,020	0,015	≥ 58,0	20,0 to 23,0	≤ 1,00	≤ 5,0	8,0 to 10,0	≤ 0,40	≤ 0,40	0,50	3,15 to 4,15	-	-
NiCr23Fe	2.4851	0,03 to 0,10	1,00	≤ 0,50	0,020	0,015	58,0 to 63,0	21,0 to 25,0	<sup>b</sup>	≤ 18,0	-	1,00 to 1,70	≤ 0,50	0,50	-	0,006	-
NiCr28FeSiCe	2.4889	0,05 to 0,12	1,00	2,50 to 3,0	0,020	0,010	≥ 45,0	26,0 to 29,0	<sup>b</sup>	21,0 to 25,0	-	-	-	0,30	-	-	0,03 to 0,09

<sup>a</sup> Elements not listed in the table may not be intentionally added to the alloy without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the alloy.

<sup>b</sup> A maximum of 1,5 % Co is allowed and counted as nickel. Reporting of cobalt is not required.

Table E.2 — Chemical composition (cast analysis) <sup>a</sup> of nickel and cobalt alloys listed in EN 10269 <sup>b</sup> and/or EN 10302

Alloy designation Name	Number	C	Si	Mn max.	P max.	S max.	Al	Cr	% by mass		Fe	Mo	Ni	Nb + Ta	Ti	Others
									Co	Cu max.						
nickel alloys																
NiCr26MoW	2.4608	0,03 to 0,08	0,70 to 1,50	2,00	0,030	0,015	-	24,0 to 26,0	2,50 to 4,0		Rem.	2,5 to 4,0	44,0 to 47,0	-	-	W: 2,50 to 4,0
NiCr20Co18Ti	2.4632	≤ 0,13	≤ 1,00	1,00	0,020	0,015	1,00 to 2,00	18,0 to 21,0	15,0 to 21,0	0,20	≤ 1,50	-	Rem.	-	2,00 to 3,0	B: ≤ 0,020 Zr: ≤ 0,15
NiCr25FeAlY	2.4633	0,15 to 0,25	≤ 0,50	0,50	0,020	0,010	1,80 to 2,40	24,0 to 26,0	-	0,10	8,0 to 11,0	-	Rem.	-	0,10 to 0,20	Y: 0,05 to 0,12 Zr: 0,01 to 0,10
NiCr29Fe	2.4642	≤ 0,05	≤ 0,50	0,50	0,020	0,015	≤ 0,50	27,0 to 31,0	-	0,50	7,0 to 11,0	-	Rem.	-	-	-
NiCo20Cr20MoTi	2.4650	0,04 to 0,08	≤ 0,40	0,60	0,020	0,007	0,30 to 0,60	19,0 to 21,0	19,0 to 21,0	0,20	≤ 0,70	5,6 to 6,1	Rem.	-	1,90 to 2,40	B: ≤ 0,005 Ti+Al: 2,40 to 2,80
NiCr20Co13Mo4Ti3Al	2.4654	0,02 to 0,10	≤ 0,15	1,00	0,015	0,015	1,20 to 1,60	18,0 to 21,0	12,0 to 15,0	0,10	≤ 2,00	3,5 to 5,0	Rem.	-	2,80 to 3,3	B: 0,003 to 0,010 Zr: 0,02 to 0,08
NiCr23Co12Mo	2.4663	0,05 to 0,10	≤ 0,20	0,20	0,010	0,010	0,70 to 1,40	20,0 to 23,0	11,0 to 14,0	0,50	≤ 2,00	8,5 to 10,0	Rem.	-	0,20 to 0,60	B: ≤ 0,006
NiCr22Fe18Mo	2.4665	0,05 to 0,15	≤ 1,00	1,00	0,020	0,015	≤ 0,50	20,5 to 23,0	0,50 to 2,50	0,50	17,0 to 20,0	8,0 to 10,0	Rem.	-	-	B: ≤ 0,010 W: 0,20 to 1,00
NiCr19Fe19Nb5Mo3	2.4668	0,02 to 0,08	≤ 0,35	0,35	0,015	0,015	0,30 to 0,70	17,0 to 21,0	≤ 1,00	0,30	Rem.	2,80 to 3,3	50,0 to 55,0	4,7 to 5,5	0,60 to 1,20	B: 0,002 to 0,006
NiCr15Fe7TiAl	2.4669 <sup>b</sup>	≤ 0,08	≤ 0,50	1,00	0,020	0,015	0,40 to 1,00	14,0 to 17,0	≤ 1,00	0,50	5,0 to 9,0	-	≥ 70,0	0,70 to 1,20	2,25 to 2,75	-
NiCr25Co20TiMo	2.4878	0,03 to 0,07	≤ 0,50	0,50	0,010	0,007	1,20 to 1,60	23,0 to 25,0	19,0 to 21,0	0,20	≤ 1,00	1,00 to 2,00	Rem.	0,70 to 1,20	2,80 to 3,2	B: 0,010 to 0,015 Ta: ≤ 0,05 Zr: 0,03 to 0,07
NiCr20TiAl	2.4952 <sup>b</sup>	0,04 to 0,10	≤ 1,00	1,00	0,020	0,015	1,00 to 1,80	18,0 to 21,0	≤ 1,00	0,20	≤ 1,50	-	> 65,0	-	1,80 to 2,70	B: ≤ 0,008
cobalt alloy																
CoCr20W15Ni	2.4964	0,05 to 0,15	≤ 0,40	2,00	0,020	0,015	-	19,0 to 21,0	Rem.	-	≤ 3,00	-	9,0 to 11,0	-	-	W: 14,0 to 16,0

<sup>a</sup> Elements not listed in this table may not be intentionally added to the alloy without the agreement of the purchaser except for finishing the cast. All appropriate precautions are to be taken to avoid the addition of such elements from scrap and other materials used in production which would impair mechanical properties and the suitability of the alloy.

<sup>b</sup> EN 10269 includes only grades NiCr15Fe7TiAl (2.4669) and NiCr20TiAl (2.4952) from this table.

## Bibliography

- [1] EN 1600, *Welding consumables – Covered electrodes for manual metal arc welding of stainless and heat resisting steels – Classification*
- [2] EN 10027-2, *Designation systems for steels – Part 2: Numerical system*
- [3] EN 10028-7, *Flat products made of steels for pressure purposes – Part 7: Stainless steels*
- [4] EN 10088-2, *Stainless steels – Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes*
- [5] EN 10088-3, *Stainless steels – Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes*
- [6] EN 10090, *Valve steels and alloys for internal combustion engines*
- [7] EN 10095, *Heat resisting steels and nickel alloys*
- [8] EN 10151, *Stainless steel strip for springs – Technical delivery conditions*
- [9] EN 10213-2, *Technical delivery conditions for steel castings for pressure purposes – Part 2: Steel grades for use at room temperature and elevated temperatures*
- [10] EN 10213-3, *Technical delivery conditions for steel castings for pressure purposes – Part 3: Steel grades for use at low temperatures*
- [11] EN 10213-4, *Technical delivery conditions for steel castings for pressure purposes – Part 4: Austenitic and austenitic-ferritic steel grades*
- [12] EN 10216-5, *Seamless steel tubes for pressure purposes – Technical delivery conditions – Part 5: Stainless steel tubes*
- [13] EN 10217-7, *Welded steel tubes for pressure purposes – Technical delivery conditions – Part 7: Stainless steel tubes*
- [14] EN 10222-5, *Steel forgings for pressure purposes – Part 5: Martensitic, austenitic and austenitic-ferritic stainless steels*
- [15] EN 10250-4, *Open die steel forgings for general engineering purposes – Part 4: Stainless steels*
- [16] EN 10263-5, *Steel rod, bars and wire for cold heading and cold extrusion – Part 5: Technical delivery conditions for stainless steels*
- [17] EN 10264-4, *Steel wire and wire products, steel wire for ropes – Part 4: Stainless steel wire*
- [18] EN 10269, *Steels and nickel alloys for fasteners with specific elevated and/or low temperature properties*
- [19] EN 10270-3, *Steel wire for mechanical springs – Part 3: Stainless spring steel wire*
- [20] EN 10272, *Stainless steel bars for pressure purposes*
- [21] EN 10283, *Corrosion resistant steel castings*
- [22] EN 10295, *Heat resistant steel castings*

## EN 10088-1:2005 (E)

- [23] EN 10296-2, *Welded circular steel tubes for mechanical and general engineering purposes – Technical delivery conditions – Part 2: Stainless steel tubes*
- [24] EN 10297-2, *Seamless steel tubes for mechanical and general engineering purposes – Technical delivery conditions – Part 2: Stainless steel tubes*
- [25] EN 10302, *Creep resisting steels, nickel and cobalt alloys*
- [26] EN 10312, *Welded stainless steel tubes and fittings for the conveyance of aqueous liquids including water for human consumption – Technical delivery conditions*
- [27] EN 12072, *Welding consumables – Wire electrodes, wires and rods for arc welding of stainless and heat-resisting steels - Classification*
- [28] EN 12073, *Welding consumables – Tubular cored electrodes for metal arc welding with or without a gas shield of stainless and heat resisting steels - Classification*
- [29] EN ISO 4957, *Tool steels (ISO 4957:1999)*
- [30] ENV 1993-1-4, *Eurocode 3: Design of steel structures – Part 1-4: General rules – Supplementary rules for stainless steels*
- [31] CR ISO 15608, *Welding – Guidelines for a metallic material grouping system (ISO/TR 15608:2000)*





---

---

## BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: [orders@bsi-global.com](mailto:orders@bsi-global.com). Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: [info@bsi-global.com](mailto:info@bsi-global.com).

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: [membership@bsi-global.com](mailto:membership@bsi-global.com).

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

### Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: [copyright@bsi-global.com](mailto:copyright@bsi-global.com).